

ONE U.S. GALLON

WARNING!

KEEP OUT OF THE REACH OF CHILDREN

See cautions elsewhere on label



ACCEPTED
JUL 14 1969
UNDER THE FEDERAL INSECTICIDE
FUNGICIDE AND RODENTICIDE ACT
FOR ECONOMIC POISON, REGISTERED
UNDER NO. 21923 SUBJECT
TO ATTACHED COMMENTS.

G.M.
International!
COPPER PAINT

ACTIVE INGREDIENTS	PER CENT
CUPROUS OXIDE	17.4
INERT INGREDIENTS	82.6
	<hr/>
	100.0%
ELEMENTAL COPPER	15.4%

W 1923 FISHING COPPER RED

International Paint Company, Inc.
NEW YORK · SAN FRANCISCO · NEW ORLEANS

FACTORIES

Melbourne.....	Australia	Genoa.....	Italy
Sydney.....	Australia	Trieste.....	Italy
Rio de Janeiro.....	Brazil	Mexico City.....	Mexico
Montreal.....	Canada	Auckland.....	New Zealand
Regina.....	Canada	Wellington.....	New Zealand
Vancouver.....	Canada	Ikeja.....	Nigeria
Copenhagen.....	Denmark	Bergen.....	Norway
Felling-on-Tyne.....	England	Bilbao.....	Spain
LeHavre.....	France	Göteborg.....	Sweden
Rouen.....	France		U. S. A.
Hamburg.....			U. S. A.
Rotterdam.....	Holland		U. S. A.
Calcutta.....	India		Venezuela

WARNING

May be fatal if swallowed. Do not get in eyes, on skin, or on clothing. Wash thoroughly after handling. Do not use or store near heat or open flame. Do not spray; apply by brush only. Close container after each use. Use with adequate ventilation.



G.M. INTERNATIONAL COPPER PAINT

A semi-hard coating of excellent anti-fouling properties for the bottoms of all wooden craft.

G. M. INTERNATIONAL COPPER PAINT is made with properties which allow for its application directly to bare wood. No special primers are required.

DIRECTIONS

Stir the paint well so that all the pigment is completely mixed with the liquid and keep it stirred.

G. M. INTERNATIONAL COPPER PAINT will not settle hard in the can and, therefore, can be easily mixed right in the container.

When applying G. M. INTERNATIONAL COPPER PAINT it is recommended that, where circumstances permit, the last coat should be allowed at least two hours to harden before the vessel is launched. It is also suggested that the launching take place within five hours after final application. However, the launching may safely be delayed for several days if during this time care is taken that the composition is not subjected to the direct rays of the sun. It is unwise to leave copper and anti-fouling paints exposed to the air for long periods.

On paintings between tides, the quick drying of G. M. INTERNATIONAL COPPER PAINT will be helpful.

Do not try to save on bottom compositions. The extent of efficiency is determined by the thickness of the coating: Therefore, when possible, three full coats are recommended.

IMPORTANT:—DO NOT INTERFERE WITH THE PROPER FUNCTIONING OF G. M. INTERNATIONAL COPPER PAINT BY ADDING ANY THINNERS OR DRIERS.

APPROXIMATE COVERAGE on average surfaces is 470 sq. ft. per gallon, 2 coats.



2693-13
ACCEPTED
Jul 14 1969

2693-63

ACCEPTED
Jul 14 1969