

"62T" INTERLUX ANTIFOULING BOTTOM PAINT RED

An excellent coating of extra strong antifouling properties which is for use on the underwater section of STEEL and WOODEN vessels.

DIRECTIONS

Stir the paint well and keep it stirred.

"62T" INTERLUX ANTIFOULING BOTTOM PAINT RED will not settle hard in the can and, therefore, can be easily mixed right in the container.


When applying "62T" INTERLUX ANTIFOULING BOTTOM PAINT RED it is recommended that, where circumstances permit, the last coat be allowed at least two hours to harden before the yacht is launched. It is also suggested that the launching take place within five hours after final application. However, the launching may safely be delayed for several days if, during this time, care is taken that the composition is not subjected to the direct rays of the sun. It is unwise to leave antifouling paints exposed to the air for long periods. Painting is often done between tides and it is then that the quick drying of "62T" INTERLUX ANTIFOULING BOTTOM PAINT RED will be helpful.

For WOOD vessels, "62T" INTERLUX ANTIFOULING BOTTOM PAINT RED is made with properties which allow for its application directly to bare wood. No special primers are required. Apply at least three coats on new work. Allow 5 hours drying time between coats.

On STEEL vessels apply 3 coats 347 "PRIMOCON" SILVER allowing 3 hours, 6 hours and overnight drying between coats. Then apply two coats of "62T" INTERLUX ANTIFOULING BOTTOM PAINT RED allowing 5 hours drying time between coats.

IMPORTANT:—DO NOT INTERFERE WITH THE PROPER FUNCTIONING OF "62T" INTERLUX ANTIFOULING BOTTOM PAINT RED BY ADDING ANY DRIERS OR THINNER.

APPROXIMATE COVERAGE on average surfaces is 400 sq. ft. per gallon, 2 coats.



ACTIVE INGREDIENTS	PERCENT
CUPROUS OXIDE	30.7%
BIS (TRIBUTYL TIN) OXIDE	2.8%
INERT INGREDIENTS	66.5%
	<u>100.0%</u>
ELEMENTAL COPPER —	27.2%
ELEMENTAL TIN —	1.1%

NET ONE U.S.


WARNING
KEEP OUT OF REACH OF CHILDREN
See other precautions on label



Interl

ANTIFOULING

BOTTOM PAINT




International Paint Company
NEW YORK, N.Y. 10004 • SAN FRANCISCO, CALIF. 94104

NET ONE U.S. GALLON


WARNING!

KEEP OUT OF REACH OF CHILDREN
See other precautions on back panel.



Interlux®
ANTIFOULING
"62T"

BOTTOM PAINT RED



ACCEPTED
JUN 5 1975
Under the Federal Insecticide,
Fungicide, and Rodenticide Act,
as amended, for the pesticide
registered under
EPA Reg. No. 2693-104

E.P.A. EST. 2693-CA-1

E.P.A. REGISTRATION NO. 2693-104 AA

FACTORIES

U.S.A. UNION, N.J.	HOLLAND	RIJS
U.S.A. SAN FRANCISCO	ITALY	G
U.S.A. NEW ORLEANS	ITALY	TR
AUSTRALIA	MEXICO	MEXICO
BRAZIL	NEW ZEALAND	AUCK
CANADA	NEW ZEALAND	WELLIN
CANADA	NIGERIA	
CANADA	NORWAY	BE
CANADA	PORTUGAL	SET
DENMARK	SCOTLAND	GLA
ENGLAND	SPAIN	B
FRANCE	SWEDEN	GOTHEN
GERMANY	VENEZUELA	MARA

WARNING!

Harmful or Fatal if swallowed. May be absorbed through skin. Causes skin irritation. Do not spray; apply by brush only.

Use with adequate ventilation.

Do not get in eyes, on skin, or clothing. In case of contact remove contaminated clothing and immediately wash skin with soap and water. If irritation persists, seek medical attention. Wash contaminated clothing before reuse. For eyes, flush with plenty of water and get medical attention. Avoid storage near food and feed products. Flammable. Keep away from heat and open flame. Clean container after each use.

Do not reuse empty container. Destroy it by perforating or crushing. Bury or discard in a safe place.

Do not contaminate water by cleaning of equipment or disposal of wastes.

International Paint Company, (California) Inc.

YORK, N.Y. 10004 • SAN FRANCISCO, CAL. 94080 • NEW ORLEANS, LA. 70186

