

ACCEPTED
JUL 7 1980
Under the Federal Insecticide,
Fungicide, and Rodenticide Act,
as amended, for the pesticide
registered under
EPA Reg. No. 2693-119

WARNING!

KEEP OUT OF REACH OF CHILDREN

See Side Panel for additional precautionary statements.

 **Interlux**®

2693-119

2693-119

PRECAUTIONARY STATEMENTS HAZARDS TO HUMANS AND DOMESTIC ANIMALS

WARNING

KEEP OUT OF REACH OF CHILDREN

Harmful if swallowed. Use with adequate ventilation. Avoid contact with skin and breathing of vapor or spray mist. Causes eye and skin irritation. **FIRST AID:** In case of contact, immediately flush eyes or skin with plenty of water for at least 15 minutes. For eyes, call a physician. If inhaled remove to fresh air. Remove and wash contaminated clothing before reuse. Wash thoroughly with soap and water after handling and before eating and smoking.

If swallowed, drink promptly a large quantity of milk, egg whites, gelatin solution or if these are not available, drink large quantities of water. Never give anything by mouth to an unconscious person. Avoid alcohol. Call a physician immediately.

ENVIRONMENTAL HAZARD

Do not contaminate water by cleaning of equipment or disposal of wastes.

PHYSICAL OR CHEMICAL HAZARD FLAMMABLE! Keep away from heat or open flame

DIRECTIONS FOR USE

It is a violation of federal law to use this product in a manner inconsistent with its labeling.

NOTE—Wear protective clothing when product is used in confined areas or applied by spraying, wear a respirator jointly approved by the Mining Enforcement and Safety Administration (formerly the U. S. Bureau of Mines) and by the National Institute for Occupational Safety and Health under the provisions of 30 CFR 11.

GENERAL DESCRIPTION

Super Bottomkote is an anti-fouling protective coating resistant to algae, barnacles and other marine fouling.

STORAGE & DISPOSAL

Do not contaminate water, food, or feed by storage or disposal. Open dumping is prohibited.

Pesticide, spray mixture, or rinsate that cannot be used or chemically reprocessed should be disposed of according to procedures approved by Federal, State, or local disposal authorities.

Container—Triple rinse (or equivalent) and dispose of in an approved landfill or bury in a safe place. Consult Federal, State, or local disposal authorities for approved alternative procedures.

SUPER
Bottomkote
A COPOLYMER EPOXY ANTIFOULING P

07/07/1980

ONE GALLON (3.785 LITERS)

1/2

SUPER BOTTOMKOTE® COPOLYMER EPOXY

GENERAL DESCRIPTION: Super Bottomkote Antifouling Paint is highly loaded with antifouling ingredients to resist fouling under the most severe conditions. It is especially recommended for southern waters where fouling conditions prevail on a "year around" basis. Because of its epoxy resin modification and high copper content, it is a tough, durable coating which can be applied several weeks before launching without fear of losing its effectiveness. Super Bottomkote is a superior product, well suited for application to large motor sailers and cruising power boats.

GENERAL PREPARATION: Surface must ALWAYS be clean and dry prior to painting. After sanding ALWAYS wipe surface clean with INTERLUX SPECIAL THINNER 216 to remove sanding residue.

GENERAL APPLICATION: Can be brushed or rolled over all other antifouling bottom paints; on fiberglass, wood and steel surfaces (per application systems below) — EXCEPT aluminum. Apply TWO coats.

MIXING INSTRUCTIONS: Shake or mix well and stir continuously while using.

THINNING INSTRUCTIONS: When brushing or rolling, do not thin bottom paints — EXCEPT for the first coat on bare wood.

DRY TIMES BEFORE: OVERCOATING - Overnight

LAUNCHING - Minimum overnight; Maximum 60 days.

THEORETICAL COVERAGE: 425 square feet per gallon.

CLEAN-UP: Use INTERLUX SPECIAL THINNER 216 for cleaning brushes and tools.

APPLICATION SYSTEMS

PREVIOUSLY PAINTED FIBERGLASS & WOOD: Remove all traces of loose paint and surface contamination. Sand thoroughly with 80-120 Grit Production Paper; wipe surface clean. Apply two coats of bottom paint.

NEW FIBERGLASS — No Sand Method: Wash entire surface with INTERLUX FIBERGLASS SOLVENT WASH 202 to remove wax and dirt, changing rag frequently. Repair scratches and dents with INTERLUX INTERFILL PUTTY 217; sand and clean repaired areas. Apply with brush or roller one thin coat of INTERLUX FIBERGLASS PRIMER 200 to ensure paint adhesion. Do not spray. Allow to cure between 2-3 hours — no more, no less. Do not sand. Apply two coats of bottom paint.

Sanding Method: Clean entire surface with INTERLUX FIBERGLASS SOLVENT WASH 202 to remove wax and dirt, changing rag frequently. Sand entire surface with 80-120 Grit Production Paper; wipe clean. Apply two coats of bottom paint.

NEW & BARE WOOD: Sand well with 80-120 Grit Production Paper; wipe surface clean. Apply first coat of bottom paint reduced with INTERLUX SPECIAL THINNER 216 (10% maximum) to penetrate the grain of wood. Fair seams with PUTTY BUG TOXIC SEAM COMPOUND 35 for use in tropical waters or SEAM COMPOUND 30 for use in other waters. Apply second and third coats of bottom paint UNREDUCED.

PREVIOUSLY PAINTED STEEL: Remove all loose paint, rust and surface contamination by sanding or using a wire brush; wipe surface clean. Touch up bare spots by roughening with 80 Grit Production Paper then spot priming with 3 coats of INTERLUX SILVER PRIMOCON 347; allow 3 hours for first coat to dry, 6 hours for the second, and overnight for the third. Apply two coats of bottom paint.

NEW STEEL: Sandblast to a near white finish; wipe surface clean. Immediately apply one thin coat of VINY-LUX PRIMEWASH 353/354 to condition the surface; allow to dry minimum of 1 hour, maximum of 24. Do not sand. Fill in all imperfections with RED HAND FILLER 4498/4499; sand filled areas smooth; wipe clean. Apply 3 coats of INTERLUX SILVER PRIMOCON 347; allow 3 hours for the first coat to dry, 6 hours for the second, and overnight for the third. Do not apply 347 above the waterline. Apply two coats of bottom paint.

E.P.A. REG. NO. 2693-119

E.P.A. EST. NO. 2693-NJ-1

®

PAINT

2/2