



WOOLSEY

TRADEWINDS®

ANTI-FOULING BOTTOM PAINT

705 RICH RED

ACTIVE INGREDIENTS: Copper Oxide 24.5%
 INERT INGREDIENTS: 75.5%

CAUTION - Keep out of reach of children. See cautions on back label.

5-21-66
 3073-1



ANTI-F
 IDEAL FOR BOTTOMS OF
 WOOD, FIBER-GLASS, PL
 WOOD, PLYBOARD, STEEL
 AND ALUMINUM

HIGHLY TOXIC—assure
 season-long protection
 against barnacles, borers,
 annelids, grass and other
 marine growths

Economical . . . easy and
 safe to apply . . . require
 minimum preparation of
 the surface

Remains bright, uniform
 smooth and colorful

Gives superior protection
 beauty and speed to hull

COMPOSITION BY WEIGHT

Copper Oxide	24.5%
Zinc Oxide	6.0%
Red Iron Oxide C.P.	8.0%
Magnesium Silicate	10.0%
705 Rosin, Fish Oil	26.0%
Aromatic Hydrocarbons	10.0%
Petroleum Thinners	15.5%
	<hr/>
	100.0%

Copper expressed as Metallic 20%
 U.S.D.A. Registration No. 3073-1



ANTI-FOULING BOTTOM PAINT

**IDEAL FOR BOTTOMS OF
WOOD, FIBER-GLASS, PLY-
WOOD, PLYBOARD, STEEL
AND ALUMINUM**

**HIGHLY TOXIC—assures
season-long protection
against barnacles, borers,
annelids, grass and other
marine growths**

**Economical . . . easy and
safe to apply . . . requires
minimum preparation of
the surface**

**Remains bright, uniform,
smooth and colorful**

**Gives superior protection,
beauty and speed to hulls**

COMPOSITION BY WEIGHT

Copper Oxide	24.5%
Zinc Oxide	6.0%
Red Iron Oxide C.P.	8.0%
Magnesium Silicate	10.0%
Rosin, Fish Oil	26.0%
Aromatic Hydrocarbons	10.0%
Petroleum Thinners	15.5%
	<hr/>
	100.0%

Copper Expressed as Metallic 20%
U.S.D.A. Registration No. 3073-1

PREPARING THE SURFACE: Wood hulls should be dry, smooth and free from grease or oil. Remove all loose paint and foreign substances. Fill seams with Woolsey 895 Underwater Seam Compound. **Metal Hulls**—Apply one coat of Woolsey Bare Metal Primecoat to all bare areas and follow with at least two complete coats of Woolsey 702 "Nevoxide" Anti-Galvanic Primer, following label directions for these products.

FIBER-GLASS—On bare (unpainted) fiber-glass, first scour and scrub with Woolsey "Shipmate" Heavy Duty Fiber-glass Cleaner or other strong abrasive agent. Rinse well with fresh water and allow to dry. Sand vigorously until all sheen on "gel coat" has been removed. Use 1/0 or No. 80 grit production paper. Wipe with clean rag moistened with paint thinner. Apply one coat of Woolsey 728/729 "MFP" Epoxy Primer, using a natural bristle brush. Allow to dry overnight.

APPLICATION: Stir contents thoroughly and mix occasionally during use to keep the high content of toxic pigment in uniform suspension.

THINNING: For first coat on new or bare wood, thin 10% with Woolsey 433 Paint Thinner, turpentine or mineral spirits. For other uses, thinning is normally not required.

NUMBER OF COATS: On New or Bare Wood, use 3 coats allowing at least 3 hours between applications. On old painted hulls in good condition and on primed metal or primed fiber-glass, apply one full coat of this paint followed with a second coat where severe fouling exists as in tropical waters.

LAUNCHING: Allow at least 4 hours after final coat before launching.

CAUTION! COMBUSTIBLE—Keep away from heat and open flame. Use with adequate ventilation. Avoid prolonged contact with skin and breathing of vapor or spray mist. Harmful if swallowed. Close can after using and keep it out of the reach of children.

5-21-68
3073-1

Keep out of reach of
cautions on back label.