

Workboat gs

ANTI-FOULING

(Insett Red)

ACTIVE INGREDIENT, Cuprous Oxide	19	3%
INERT INGREDIENT:	80	7%

[illegible]

100 FLEET RED ANTI-FOULING

An economical anti-fouling copper bottom paint for protection against barnacles, tentacles, sponges, hydroids, algae and other marine growth. For use on wood. Also excellent for fishermen's gear such as lobster buoys, pots, stakes, etc. Easy to apply, it remains uniformly bright and smooth.

**STIR CONTENTS THOROUGHLY AND MIX OCCASIONALLY DURING USE TO KEEP TOXIC
PIGMENT IN UNIFORM SUSPENSION.**

SURFACE PREPARATION: Remove all old paint, grease, oil, dirt and foreign substances using scraper, wirebrush or sandpaper. Bare metal surfaces must be primed before paint application may be then over coated with two full coats. Hulls in poor condition should be sanded to bare surface and procedure is as follows:

WOOD: Apply three full coats allowing 3 hours dry between coats. The last coat should be applied 5-6 hours before launching.

THINNING: For first coat on bare wood thin 10% with 1:1 thinner. (Thinning not normally required.)

COVERAGE: One coat at full strength covers 500 square feet; in water

LAUNCHING: The final coat should be applied 5-6 hrs before launching.

CAUTION! COMBUSTIBLE—Keep away from heat and open flame. Use with adequate ventilation. Do not get in the eyes. If skin is irritated, avoid breathing spray mist. Should contact, flush eyes with water and flush skin with light mineral oil, then wash with soap and water. If irritation persists, obtain medical attention. Harmful if swallowed. **Close container after using. Not for use or storage in or around the home environment. Keep out of the reach of children. Do not reuse empty container. Destroy by peeling or crushing. Bury or discard in a safe place. Do not contaminate water by cleaning of equipment or disposal of wastes.**

MADE IN U.S.A. WOOLSEY MARINE INDUSTRIES, Inc., BROOKLYN, N.Y. 11231 "WOOLSEY" Reg. Trade Mark U.S. Pat. Off. & Abroad.