



MARINE FINISHES
"CUPROTEX"
WOOD PRESERVATIVE

This liquid preservative gives extra years of useful life when applied to lumber in sound condition—whether for new work or repairs, above or below the waterline. Penetrates well, leaving a chemical barrier which resists rot and decay by protecting the wood fibres against destructive fungi growths and the entrance of borers. "Cuprotex" produces a green stained effect due to its copper base and should be over-coated with paint or other pigmented finish. Note: if wood is to be finished with a clear or transparent coating, use Woolsey "Halt" Wood Preservative which is formulated with a colorless zinc base.

DIRECTIONS FOR USE

SURFACE—New or raw wood should be as dry and clean as possible.

APPLICATION—Use CUPROTEX as received. Apply liberally by brush or dip method (immersing for at least 3 minutes).

COVERAGE—The quantity required depends on the lumber and method of applying. Soft wood such as pine requires about 1 gallon for 250 sq. ft. whereas harder woods require considerably less material.

DRYING—Allow at least 24 hours drying before painting. Longer drying periods are necessary when wood has been dipped.

EXTERIOR PAINTING—Use CUPROTEX Green.

EXTERIOR VARNISHING—Use HALT Clear.

Exposed lumber is not only beautified by applying paint or varnish over CUPROTEX but the fungicidal properties are preserved and locked in against the action of sun and rain.

UNDERWATER PAINTING—Use CUPROTEX Green. Unpainted wooden boat bottoms are safeguarded against biological destruction through the application of CUPROTEX followed by Woolsey bottom paints such as TRADEWINDS, NEPTUNE, ANTI-FOULING HARD RACING FINISH or CAWLUX FRESH WATER FINISHES. Caution—not to be used under VINELAST ANTI-FOULING RACING FINISH.

CAUTION! COMBUSTIBLE—Keep away from heat and open flame. USE WITH ADEQUATE VENTILATION. Avoid prolonged contact with skin and breathing of vapor or spray mist. Do not take internally. Harmful if swallowed. Close can after using and keep it out of the reach of children.

WOOLSEY

CUPROTEX
TRADE MARK
WOOD PRESERVATIVE

Protects Against Rot, Decay, Borers, Fungi
Water-Repellent—An Ideal Base For Paint

749 GREEN

ACTIVE INGREDIENTS: Copper Napthenate 20.0%
 Alkyl Amine Salt of Tetrachlorophenol 1.0%

INACTIVE INGREDIENTS: Mineral Spirits 79.0%
 Contain 2% copper expressed as metallic

CAUTION—Keep out of reach of children. See cautions on back label.

U.S.D.A. Registration No. 3073-15

Dec-3-1971

3073-15