




ONE QUART U.S. MEASURE

GLOUCESTER



RED PLASTIC ANTIFOULING PAINT

FOR PREVENTION OF WORMS, BARNACLES AND ALGAE ON SHIP & BOAT BOTTOMS IN SALT WATER

ACTIVE INGREDIENT	
Cuprous Oxide*	30.1%
INERT INGREDIENTS	69.9%
	<hr/> 100.0%

*TOTAL COPPER METAL	26.8%
(from Cuprous Oxide)	

505c RED

CAUTION

KEEP OUT OF REACH OF CHILDREN

UNDER THE FEDERAL FUNGICIDE AND...

Other
"GLOUCESTER"
Marine Finishes
and Specialties

Deck and Floor Paint
Spar Varnish
Yacht Whites
Hull & Topside Paints
Seam Compounds
Epoxy Enamels
and Compounds
Seafood-Hold Paints
Anticorrosive
Metal Primers
Engine Enamels

NEW AND STRIPPED WORK

Previously painted bottoms on which the old paint is in good condition and firmly attached may be recoated after sanding off all loose dirt. Where old paint is loose and flaking in large areas, strip it off and proceed as for new unpainted work.

This copper paint can be applied directly to wood bottoms after sanding smooth. To insure adhesion to fiberglass bottoms, they should be primed with one coat of B370 or 375 Epoxy Primer, in accordance with directions for that material, before applying copper paint. Prime steel bottoms with two coats 407 Shipbottom Primer, and aluminum bottoms with two coats 110 or 115 Primer before using copper paint.

Stir copper paint thoroughly with a flat paddle before using and during application. Apply two coats to clean, dry surface and allow at least 4 hours drying time between coats and before launching. Thin only if absolutely necessary to restore free brushing consistency. A little turpentine or paint thinner, well stirred in, can be used for this purpose and for cleaning brushes and equipment. Use no other materials.

CAUTION - FLAMMABLE

Do not use, pour, spill or store near heat or open flame.

THIS PAINT CONTAINS COPPER AND OTHER COMPOUNDS HARMFUL if swallowed and it is sold for use ONLY on ship and boat bottoms for the prevention of marine fouling. Do not use it in any household application. Avoid breathing vapor or spray mist and contact with skin. Wash immediately with soap and water in case of contact with skin. Use protective mask when dry-sanding. Avoid contamination of feed and foodstuffs.

Keep container closed when not in use. Keep out of reach of children.

USE WITH ADEQUATE VENTILATION.

U.S.D.A. Registration No. 3482-28

GP Form 505-171

Other
"GLOUCESTER"
Marine Finishes
and Specialties

Deck and Floor Paint
Spar Varnish
Yacht Whites
Hull & Topside Paints
Seam Compounds
Epoxy Enamels
and Compounds
Seafood-Hold Paints
Anticorrosive
Metal Primers
Engine Enamels