

# ATCO

1220

## TAR and CREOSOTE

A black preservative especially for painting shingle roofs. Retards cracking and curling of shingles. Is also excellent protection for fence posts and all wood which is to come in contact with the ground. Fence posts to be properly protected against wood rot, fungi, termites and powder post beetles should be peeled of bark, well seasoned, dry and dipped for 12 to 18 hours. Wood which is to come in contact with the ground should receive at least two coats by brush or spray method or dipped for at least three minutes.

**Active Ingredients:**

Refined Coal Tar	70%
Light Creosote Oil	30%

EPA Reg. No. 3486-1

**CAUTION: KEEP OUT OF REACH OF CHILDREN**

May cause skin irritation. Avoid prolonged or repeated contact with skin. Vapor harmful. Use in well ventilated places and precaution should be taken to avoid prolonged breathing of vapors. Harmful or fatal if swallowed. Call a physician immediately. Keep away from open flames and electrical equipment.

Content 1 Gallon



American Tar Co.  
SEATTLE