

ATCO

1405

PENTA WOOD PRESERVATIVE

FEDERAL SPECIFICATION TT-W-570

A standard ready-to-use pentachlorophenol preservative for wood. Can be painted over. A good preservative for posts, poles, or lumber that is to come in contact with the ground or is exposed to the elements. Fence posts to be properly protected against wood rot, fungi, termites and powder post beetles should be peeled of bark, well seasoned, dry and dipped for 12 to 48 hours. Lumber to be in contact with the soil should receive at least 2 coats by brush or spray method or dipped for at least 3 minutes. Covering capacity approximately 150 to 200 square feet per gallon depending on porosity of wood and method in applying. For sealing and treating wood where a dry, odorless, paintable surface is desired use ATCO #1412 PENTA PRESERV-A-SEAL.

| | |
|---|---------|
| ACTIVE INGREDIENTS 100% | |
| Pentachlorophenol | 4.25 % |
| Other Chlorophenols and Related Compounds | 0.75 % |
| Petroleum Distillates | 95.00 % |

USDA Reg. No. 3486-8

CAUTION: KEEP OUT OF REACH OF CHILDREN

THIS PRODUCT IS POISONOUS TO FISH AND WILDLIFE

May cause skin irritation. Do not get in eyes, on skin or clothing. Do not breathe vapor or spray mist. In case of contact with eyes, flush with water for at least 15 minutes. In case of contact with skin, wash immediately with soap and water. Use in well-ventilated places. Liquid or spray drift can kill or defoliate plants. Keep away from open flames and electrical equipment. Harmful if swallowed or absorbed through skin.

Content 1 Gallon



ACCEPTED

6-28-67

UNDER THE FEDERAL INSECTICIDE
FUNGICIDE AND RODENTICIDE ACT
FOR ECONOMIC POISON REGISTR-
ED UNDER NO. 3486-8

ACCEPTED WITH COMMENTS

ATCO

1405

PENTA WOOD PRESERVATIVE

FEDERAL SPECIFICATION TT W-570

Use it under the following conditions: Use pentachlorophenol preservative for wood. Can be painted over. A good preservative for posts, poles, or lumber that is to come in contact with the ground or is exposed to the elements. Lumber posts to be properly protected against wood rot, fungi, termites and powder post beetles should be preservative treated, well seasoned, dry, and dipped for 12 to 48 hours. Lumber to be in contact with the soil should receive at least 2 coats by brush or spray method or dipped for at least 10 minutes. Coverage capacity approximately 150 to 200 square feet per gallon depending on porosity of wood and method of applying. For sealing and treating wood where a dry, colorless, impervious surface is desired use ATCO #1412 PENTA PRESERVATIVE.

ACTIVE INGREDIENTS 100%

| | |
|---|--------|
| Pentachlorophenol | 4.25% |
| Other Chlorophenols and Related Compounds | 0.75% |
| Petroleum Distillates | 95.00% |

USDA Reg. No. 3486-B

CAUTION: KEEP OUT OF REACH OF CHILDREN

THIS PRODUCT IS POISONOUS TO FISH AND WILDLIFE

May cause skin irritation. Do not get in eyes, on skin or clothing. Do not breathe vapor or spray mist. In case of contact with eyes, flush with water for at least 10 minutes. In case of contact with skin, wash immediately with soap and water. Use in well-ventilated places. Liquid or spray drift can kill or injure plants. Keep away from open flames and electrical equipment.

Harmful if swallowed or absorbed through skin.

Content 1 Gallon



American Tar Co.
SEATTLE