



ONE U.S. STANDARD GALLON

IMPERIAL MEAS. 132 FL. OZ.



# DOLPHIN Copperpac



(For Fresh Water)

ACCEPTED

## WARNING!

KEEP OUT OF REACH  
OF CHILDREN  
HARMFUL OR FATAL  
IF SWALLOWED

See back panel for  
additional required  
Caution Statements

## 9126 Anti-Fouling Bottom Paint TYPE 3

NET CONT. 128 FL. OZS. (1 GAL.)

IMPROVED  
COLOR

<b>9126 Copperpac Type 3</b>		
<b>Pigment:</b>		<b>58.3</b>
90.5% Cuprous Oxide		
9.5% Dichlone		
<b>Vehicle:</b>		<b>5.6</b>
100% Phenolic Resin, Ester Gum, Hardened Rosin, Tung and Linseed Oils		
<b>Volatile:</b>		<b>36.1</b>
41.2% Petroleum Thinner		
36.8% Aromatic Thinner		
22.0% Turpentine		
		<b>100.0</b>
<b>Active Ingredients</b>	<b>By Weight</b>	
Cuprous Oxide		<b>51.2</b>
Dichlone		<b>5.5</b>
(2.2 dichlone 1.4 naphthoquinone)		
Net Ingredients		<b>43.3</b>
Copper Expressed As Metallic	11.1	<b>100.0</b>

MANUFACTURED BY THE DOLPHIN PAINT & CHEMICAL COMPANY TOLEDO 3, OHIO, U.S.A.


S. 132 FL. OZ.



" DO IT RIGHT - WITH *Dolfinite* "



(For Fresh Water)



IMPROVED COLOR

<b>9126 Copperpac Type 3</b>		
<b>Pigment:</b>		<b>58.3%</b>
90.5% Cuprous Oxide		
9.5% Dichlone		
<b>Vehicle:</b>		<b>5.6%</b>
100% Phenolic Resin, Ester Gum, Hardened Rosin, Tung and Linseed Oils		
<b>Volatile:</b>		<b>36.1%</b>
41.2% Petroleum Thinner		
36.8% Aromatic Thinner		
22.0% Turpentine		
<b>Active Ingredients</b>	<b>By Weight</b>	<b>100.0%</b>
Cuprous Oxide	51.2%	
Dichlone (2, 3-dichloro — 1, 4-naphthoquinone)	5.5%	
<b>Inert Ingredients</b>		<b>43.3%</b>
Copper Expressed As Metallic (L.)	44.4	100.0%

**DOLFINITE COPPERPAC 9126** (Type 3) Anti-Fouling Bottom Paint for use in fresh water areas was developed jointly by the manufacturer and The Marine Laboratory of the University of Miami, Florida.

Two coats of Copperpac will insure anti-fouling protection for a full boating season. Copperpac is unique in that it is consistent in performance in all places and seasons, and has a controlled toxic release rate and leaching rate which are constant and above the critical rate at all times. Copperpac can be applied during storage in anticipation of early launching. Boats painted with Copperpac may be launched with the film either wet OR dry.

Boats protected with Copperpac should be scrubbed with a stiff brush and fresh water immediately upon removal from the water to remove the bacterial slime before it oxidizes and, thereby, protect the anti-fouling qualities.

**DIRECTIONS FOR APPLICATION**

The ease of application by brush, roller or spray makes for reduced preparation and maintenance time and costs. Copperpac dries to a smooth, flat, reddish-brown film. Shake thoroughly before and stir frequently while using to insure even and complete distribution of the anti-fouling ingredients. **THINNING IS NOT RECOMMENDED OR REQUIRED.** Should a partially used can require thinning, add only a small amount of pure gum turpentine — any other material may completely destroy the effectiveness of Copperpac.

**WOOD** — The surface should be clean, dry and well sanded. No undercoat is required. Apply two coats to insure complete protection: both coats may be applied during the same day allowing 4 hours drying time between coats.

**SUGGESTION** — For added protection we suggest a coat of Dolfinite Wormicide, which contains Biomet, be applied directly to the bare wood before the application of Copperpac. This will insure protection from marine worms, borers, teredos or other marine growth in the event of mars, scrapes or scuffs.

**FIBER GLASS** — Fiber Glass must be thoroughly and carefully cleaned of all waxes, mold release agents, etc. by cleaning thoroughly with a strong solvent; sanded vigorously to provide a roughened surface for good adhesion. No undercoater is required — apply two coats of Copperpac allowing 4 hours between coats.

**STEEL AND ALUMINUM** — Aluminum and steel boats require a complete system of anti-corrosive and galvanic protection barrier coats prior to the application of Copperpac. Ask your marine dealer for our booklet giving complete and detailed instructions for applying Copperpac to steel and aluminum boats.

**BRUSHES** - May be cleaned with turpentine or mineral spirits.

**WARNING: CONTAINS XYLOL, COPPER AND DICHLONE.** Keep away from heat, sparks and open flame. Avoid contact with skin and eyes. Avoid inhalation. Close container after each use. **USE WITH ADEQUATE VENTILATION.**

**ANTIDOTE:** If swallowed, do not induce vomiting. **CALL PHYSICIAN IMMEDIATELY.**

U.S.D.A. Registration No. 3658-3

ACCEPTED WITH COMMENTS

COMPANY TOLEDO 3, OHIO, U.S.A.

QUALITY PRODUCTS SINCE 1885