

3658-13  
**ACCEPTED**  
 5/5/71  
 UNDER THE FEDERAL INSECTICIDE  
 FUNGICIDE AND RODEFICIDE ACT  
 ECONOMIC POISON REGISTRY  
 UNDER NO. 31.37  
 AS ATTACHED COMMENTS.

ONE U.S. STANDARD GALLON

IMPERIAL MEAS. 132 FL. OZ.

**DOLFINITE**®

**COORALAC**



**DANGER!**  
 KEEP OUT OF REACH  
 OF CHILDREN  
 See back panel  
 for additional  
 DANGERS

**9302  
 Yellow**

9302 YELLOW	
<b>Pigment:</b>	23.4%
61.3% Titanium Dioxide	
11.7% Meta-Xylidide Yellow	
25.6% Tri-butyltin Fluoride	
1.4% Inert	
<b>Vehicle:</b>	19.70%
Vinyl Resin — 8.75%	
Resin — 9.85%	
Diocetyl Phthalate — 1.10%	
<b>Volatile:</b>	56.9%
58.3% Ketones	
41.7% Aromatic Thinner	
	100.0%
<b>Active Ingredients:</b>	By Weight
Tri-butyltin Fluoride	6.00%
Inert Ingredients:	94.00%
	100.00%
(Tin as metallic 2.31%)	

NET CONT. 128 FL. OZ. (1)

PRODUCED BY **THE DOLPHIN PAINT & CHEMICAL COMPANY** TOLEDO, OHIO

66  
 C O R T E S I O F P R I N T E R S  
 K C  
 C P C

EAS 132 FL. OZ.

# "DO IT RIGHT - WITH Dolfinite"

## INSTRUCTIONS FOR USE

**DOLFINITE COLORPAC ANTI-FOULING PAINT** is a new bottom coating designed for control of many marine organisms. This paint is based on bioMeT\*, a new powerful anti-fouling ingredient. It can be applied to fiberglass, wood, aluminum and steel hulls. Recoating is possible in three or four hours, but paint should be allowed to dry overnight before boat launching. Apply the paint liberally with a full brush or enamel-type roller. **DO NOT SPRAY.**

**FIBERGLASS HULLS.** Remove all mold release agents by wiping thoroughly with a suitable solvent (Xylol); sand thoroughly with medium grade sandpaper and apply two coats of Colorpac. For painting over old work, follow instructions for recoating wood.

**WOODEN HULLS:** On new wood, apply two full coats directly to the wooden surface. On old work, Colorpac anti-fouling paint may be applied over clean, dry, firm surfaces provided the previous paint was a vinyl or epoxy type. All other types of paints should be removed to the bare wood.

**METAL HULLS:** Aluminum should be etched with Alumiprep, coated with a wash coat primer system (Dolfinite 9660-9661) and then two coats of Colorpac. Steel should be cleaned by sandblasting or grinding, treat with Metalprep and followed by two coats of Colorpac. Apply Colorpac by roller or brush. **DO NOT SPRAY.**

**DANGER! MAY CAUSE SEVERE EYE BURNS. MAY BE FATAL  
IF SWALLOWED. MAY CAUSE SKIN IRRITATION.**

Do not get in eyes, on skin, or on clothing. Avoid breathing of vapor or spray mist. Keep away from heat, sparks and open flame. Use with adequate ventilation. Close container after each use.

May cause severe eye damage. Wear goggles or face shield when using. In case of contact, immediately flush eyes with plenty of water for at least fifteen minutes and get prompt medical attention; wash skin with plenty of soap and water. Wash contaminated clothing before re-use. **If swallowed, CALL PHYSICIAN IMMEDIATELY.**

U.S.D.A. Registration No. 3658-13



<b>9302 YELLOW</b>	
<b>Pigment:</b>	<b>23.4%</b>
61.3% Titanium Dioxide	
11.7% Meta-Xylidide Yellow	
25.6% Tri-butyltin Fluoride	
1.4% Inert	
<b>Vehicle:</b>	<b>19.70%</b>
Vinyl Resin — 8.75%	
Rosin — 9.85%	
Diocetyl Phthalate — 1.10%	
<b>Volatile:</b>	<b>56.0%</b>
58.3% Ketones	
41.7% Aromatic Thinner	
	<b>100.0%</b>
<b>Active Ingredients:</b>	<b>By Weight</b>
Tri-butyltin Fluoride	6.00%
Inert Ingredients:	94.00%
	<b>100.00%</b>
(Tin as metallic 2.31%)	

COMPANY TO BE OWNED

QUALITY PRODUCT SINCE