

June 76, 1973

3658-42

★ QUALITY PRODUCT ★

# DOLFINITE 9146 DOUBLE

DOLFINITE DOUBLE DUTY UTILITY BOTTOM PAINT is a tough, serviceable bottom paint for boat owners. It is easily applied, straight from the can, and dries quickly. Boat should be launched within 24 hours of drying. Surface should be clean, dry and free of any oil or grease. All worn or bare spots should be touched up thoroughly and stir frequently to insure thorough mixing. Two coats recommended.

**WOOD BOATS:** No undercoater required. Apply with roller or spray. Mineral spirits should be used for cleaning.

**FIBERGLASS:** Thoroughly and carefully sandblast and wipe clean with Dolfinite 1001 thinner before application.

**STEEL AND ALUMINUM:** Application to steel and aluminum requires a galvanic and/or electrolysis barrier coat. Apply Wash Coat Primer 9660 or 9662 or 9670.

**CAUTION: CONTAINS COPPER AND PETROLEUM.** Keep away from heat, sparks and open flame. Avoid contact with skin, eyes, nose, mouth and clothing. In case of contact with warm water. Use with adequate ventilation. Do not reuse empty container. Destroy it by proper disposal.

Do not contaminate water by cleaning of container or excess material.

KEEP OUT OF THE REACH OF CHILDREN

E. P. A. Registered

## WARNING!

KEEP OUT OF REACH  
OF CHILDREN

See Back Panel for  
additional required  
Caution Statements

## 9146 Double Duty Blue Anti-Fouling

NET CONT. 32 FL. OZ. (1 QT.)

Active Ingredients:	31.34%
Cuprous Oxide	30.63%
Tributyltin Resinate	0.71%
Inert Ingredients:	68.66%
	100.00%

(Copper as Metallic—27.21%)

MANUFACTURED BY THE DOLPHIN PAINT & CHEMICAL COMPANY TOLEDO, OHIO 43603 U.S.A.

DO IT RIGHT - WITH DOLFINITE

★ QUALITY PRODUCTS SINCE 1885 ★

**DOLFINITE 9146 DOUBLE DUTY BLUE ANTI-FOULING**

DOLFINITE DOUBLE DUTY UTILITY BOTTOM PAINT has been formulated to provide boat owners a tough, serviceable bottom paint with good protective characteristics. It is easily applied, straight from the can, by brush, roller or spray. Requires overnight drying. Boat should be launched within 24 hours after application of last coat. Surface should be clean, dry and free of any loose paint, scale or other foreign matter. All worn or bare spots should be touched up prior to application of first coat. Shake thoroughly and stir frequently to insure thorough distribution of protective ingredients. Two coats recommended.

**WOOD BOATS:** No undercoater required. Apply material as received by either brush, roller or spray. Mineral spirits should be used for thinning.

**FIBERGLASS:** Thoroughly and carefully sand hull with a medium coarse sand paper and wipe clean with Dolfinite 1001 thinner before application.

**STEEL AND ALUMINUM:** Application to metal hulls requires a complete system of galvanic and/or electrolysis barrier coats. Metal must be clean, preferably sand blasted. Apply Wash Coat Primer 9660 9661, followed by two barrier primer coats, 9662 or 9670.

**CAUTION:** CONTAINS COPPER AND PETROLEUM DISTILLATE. Harmful if swallowed. Keep away from heat, sparks and open flame. Avoid contact with skin and breathing of vapor and spray mist. In case of contact, immediately wash skin with soap and warm water. Use with adequate ventilation. Close container after each use. Do not reuse empty container. Destroy it by perforating or crushing. Bury or discard in a safe place.

Do not contaminate water by cleaning of equipment, or disposal of wastes.

**KEEP OUT OF THE REACH OF CHILDREN**

E. P. A. Registration No. 3658-42

" DO IT RIGHT - WITH *Dolfinite* "