



# No-Rott Concentrate

(TRADE MARK)

USDA REGISTRATION No 4012 11

ACTIVE INGREDIENT  
Copper Naphthenate 25%  
2% Metallic Copper  
Petroleum Distillates 75%



MEETS U. S. NAVY  
SPECIFICATION 52 W 5  
MEETS FEDERAL SPEC  
O-D-406 NAVY SHIPS  
MEETS MIL SPEC. MP 906  
MEETS U. S. ARMY SPEC. 100-17  
Commercial Standard - CS-152-48  
Wood Preserver, Water Repellant

HARMFUL IF SWALLOWED

**CAUTION: KEEP OUT OF REACH OF CHILDREN**

INFLAMMABLE — Do Not Spray Near or Toward Open Flame Do Not Smoke While Spraying.

**WARNING** Avoid contact with skin, eyes, and clothing Do not take internally In case of contact with dry material or its solution, immediately wash skin with soap and plenty of water, for eyes flush with plenty of water for at least 15 minutes and get medical attention

Apply by spraying, brushing or dipping. NO-ROTT checks the rotting effects of water and fungi and treated wood is protected against the attack of termites and other wood-destroying insects.

NO-ROTT is harmless to plants and is ideal for treating wooden posts that come into contact with Roots and Stems of growing plants as well as with the moist earth.

**DIRECTIONS** Spray, brush or immerse surface to be treated, using one gallon NO-ROTT to 100 sq. ft. of rough lumber or one gallon to 100 sq. ft. of finished wood. When using the immersion system wood should be immersed for at least 3 minutes, one dip is all that is necessary. In all three systems particular care should be given to cracks, knot-holes and board end areas to see that they are properly treated. A second coat of NO-ROTT is ideal for these areas. To prevent bleeding, put a coat of shellac over treated area before painting. Do not over saturate cloth with NO-ROTT since this will cause stickiness when dry. just apply enough NO-ROTT to dampen the cloth. In treating duck, use one gallon to each 90 sq. ft. of standard 8 oz. duck. Wood that is to be in contact with ground should receive a minimum of (2) flowing coats if treated by brushing or spraying.

NO-ROTT may be diluted 1 Barrel NO-ROTT plus 3 Barrels Mineral Spirits to make Four Barrels of 2 per cent Metallic Copper Solution. When used at this dilution wood should be immersed at least 12 hours for protection against Termites, Rot and Mildew.

Net Contents ————— Gallons

