

NET CONTENTS
55 U. S. GALLONS

ACTIVE INGREDIENTS	PER CENT
PETROLEUM DISTILLATES	90
COPPER NAPHTHENATE	10
TOTAL	100

Copper as Metal 1 per cent.

Copp-A-Cote

PRESERVATIVE COPPER - NAPHTHENATE

PROTECTS

WOOD • CANVAS • ROPE • BOATS

HELPS PREVENT

WOOD ROT • TERMITES • FUNGUS

This Ready for Use Copper Naphthenate complies with all requirements of Commercial Standard CS152-48, as Developed by the Trade User under the Procedure of The National Bureau of Standards, and Issued by The U. S. Department of Commerce. Complies with Military Specification, Mil-T-11293.

DIRECTIONS FOR APPLICATION AND USE: May be brushed, sprayed or dipped. **NEW WOOD NOT TO BE PAINTED.** COPP-A-COTE may be applied with a brush, spray or thoroughly dipped. If brushed or sprayed allow the first coat to dry completely and apply a second coat. If dipped allow three minutes per inch of thickness. "EPA Reg. No. 4499-4".

NEW WOOD TO BE PAINTED OR OLD WOOD TO BE TREATED AND REPAINTED. Clean the surface and apply one generous coat with a brush or spray and allow to completely dry. Then apply two coats of paint. One coat will not cover. Fence posts, poles and similar wood members should be free of bark, dry and well seasoned and immersed in COPP-A-COTE for 12 to 48 hours to be effective against wood rotting fungi. All lumber intended to be in contact with the soil should be dipped for a minimum of three minutes per inch of thickness. Nets, Cordage, Fabrics and similar articles should be dipped until wet through. **WOOD TO BE TREATED FOR TERMITES . . .** Apply two heavy coats with a spray or brush to all lumber that is to come in contact with the ground. Protection for existing wooden structures is limited to such pest as wood rot, powder post beetles, and carpenter ants.

BOATS AND MATERIAL FOR BOATS. COPP-A-COTE may be applied by brush or dipped. Apply two coats if brushed or sprayed. If dipped allow a minimum of three minutes per inch of thickness. All wood must be completely dry before applying COPP-A-COTE. **NOTE:** All materials to be treated with COPP-A-COTE must be completely dry before applying, as COPP-A-COTE is insoluble in water.

CAUTION: Keep Out Of Reach Of Children

"Petroleum oils tend to dry out the skin. In case of contact wash thoroughly with soap and water."

"Harmful if swallowed. Avoid contact with skin and eyes."

"Do not reuse empty drum. Return to drum conditioner or destroy by perforating or crushing and burying in a safe place."

"Do not contaminate water by cleaning of equipment, or disposal of wastes."

"DO NOT USE, POUR, SPILL OR STORE NEAR HEAT OR OPEN FLAME"

MANUFACTURED AND PACKAGED BY

FLOYD PINE PRODUCTS COMPANY

ANDALUSIA, ALABAMA 36420

4499-4
ACCEPTED

Dec 13 1972

INDUSTRIAL
REGULATORY ACT