

ACCEPTED
Date 1/1/63
UNDER THE FEDERAL INSECTICIDE
FUNGICIDE AND ROENTGEN ACT
AS ECONOMIC POISON REGISTERED
E.P. NO. 4861-2

EPA Reg. No. 4861-2

ONE GALLON

C & P CREOSOTE

OIL
WOOD PRESERVATIVE

Meets AWWA #1 & ASTM D-390 Specifications

Active Ingredient (Coal-Tar Creosote)	97.0%
Inert Ingredients	3.0%

DIRECTIONS

Use material as it comes from can. Do not thin for dipping or spraying. Sleepers, joints, jambs, window frames, other mill work and timber should be treated before installation for best results. At least two flowing coats should be used on timbers which are to come in contact with the ground or masonry.

FOR BRUSH: Apply liberally using as many coats as necessary to secure penetration desired. Protection is dependent on good penetration. At least two flowing coats should be used on timbers which are to come in contact with the ground or masonry. Timbers and other heavy wood members should be free of bark, dry and well-seasoned and be immersed for 12 to 48 hours when treated by the dip method.

Creosote Oil is especially effective as a Wood Preservative in protecting wood against fungus growths which cause wood rot and stain, Termites and Powder Post Beetles.

WARNING

HARMFUL IF SWALLOWED
CAUSES SKIN IRRITATION.

Irritation accentuated by light. Avoid contact with skin and clothing. Avoid breathing of vapor. Use only with adequate ventilation. Do not reuse container. Destroy when empty.

Do not contaminate water by cleaning of equipment or disposal of wastes.

Do not spray near or toward an open fire.

Clarke and Proctor Turpentine Company

Fayetteville, N. C.

Phone 483-7469

P. O. Box 194

CAUTION: Keep out of reach of Children.