

i

1

ł



. . . . . .

AG . 3

## MARINE FINISHES COPPER BRONZE

One Quart U.S. Measure DIRECTIONS

A very effective yacht and racing bottom paint. Its smooth, hard finish is designed to minimize friction. MARINE FINISHES COPPER BRONZE is highly recommended for application on the bottom or contact side of wooden water skies.

PREPARATION OF SURFACE: The surface should be dry, clean. smooth and free of grease and oil. Thoroughly remove all loose paint and other foreign substances by scraping and sanding. Where finish is in poor condition, use paint and varnish remover. Metal surfaces must be primed with Metal Primer.

APPLICATION: Remove can cover, carefully lift out the upper compartment containing the powdered copper paste and stir this paste into the vehicle until thoroughly dispersed. Stir occasionally during the application of the paint. Do not add any other oil, varnish or paint. Do not add paint thinner unless the paint becomes too thick and then not more, and preferably less, than 1/2 pint of V-THINNER per gallon. On previously painted surfaces in good repaintable condition, only two coats are required. On new work and on surfaces from which all paint has been removed, three coats are necessary.

DRYING TIME: Allow eight hours drying between coats and before launching.

## C&M CHEMICAL COMPANY

A DIVISION OF THE VALSPAR CORPORATION MINNEAPOLIS, MINNESOTA 55415

MARINE FINISHES COPPER BRONZE 3221 Composition by Weight Per Cen 100.0 100.0 010677

LATE.

other containers. Close con-

WARNING. HARMFUL OR FATAL IF SWALLOWED, DO NOT INDUCE VOMITING. CALL PHYSICIAN. CONTAINS PETROLEUM DISTIL-

WARNING: FLAMMABLE Keep away from heat and open flame. Use with adequate ventilation. Avoid breathing of vapor or spray mist. Do not transfer contents to bottles or

tainer after each use. DO NOT TAKE INTERNALLY.

· • .



## MARINE FINISHES

## **COPPER BRONZE 3221**

U.S.D.A. Reg. No. 5334-6

1 QUART

WARNING!See back panel for additional required warnings. **KEEP OUT OF REACH OF CHILDREN** 

Active In**gredients** Metallic Copper....24.7% Inert Ingredients...75.3% 100.0%