

WART-COLOR

PEN-CO-NAP WOOD PRESERVATIVE

25% COPPER NAPHTHENATE

GREEN VC-91

DANGER!

HARMFUL OR FATAL IF SWALLOWED
KEEP OUT OF REACH OF CHILDREN

See cautions elsewhere on label.

1 U.S. GALLON

4 PINTS

ACCEPTED

Apr. 1, 1967

Active Ingredient:	
Copper Naphthenate	25%
Inert Ingredient:	
Petroleum Distillate	75%
Total	100%
Of the total, 2% is metallic copper.	

This ready to use PEN-CO-NAP complies with all requirements of Commercial Standards CS 152-48, as developed by the trade in cooperation with the National Bureau of Standards of the U.S. Department of Commerce.

U.S.D.A. REG. NO. 5695-3

Tip:
FOR THE mineral spray retention on joints with posts and so on. **LUMBER** (at least 1 coat will be required). Wood can be painted with brush or spray. **TEINTS,** dip method of preservation. **FOR THE** wood with joints wide, but rate of use.



LOR

P
ATIVE
NATE

WARRIOR-GOODING

Active Ingredient:	
Copper Naphthenate	25%
Inert Ingredient:	
Petroleum Distillate	75%
Total	100%
Of the total, 2% is metallic copper.	

This ready to use PEN-CO-NAP complies with all requirements of Commercial Standards CS 152-48, as developed by the trade in cooperation with the National Bureau of Standards of the U.S. Department of Commerce.

U.S.D.A. REG. NO. 5695-3

WED
REN

Timber should be dry. If necessary to cut wood after treatment, scrub cut surfaces thoroughly.

FOR TREATING FENCE POSTS. This product may be diluted with two parts kerosene or mineral spirits for fence post treatment, provided posts are thoroughly soaked to allow maximum retention of preservative. Use only posts which have been paled and well seasoned. Fill an open barrel with posts and pour the preservative in, until barrel is full. Soak 24 hours, then turn the posts end for end and soak an additional 24 hours. The posts may be set out any time thereafter.

LUMBER, SASH, FRAMES, TOOL HANDLES, ETC. should be sprayed, painted, or dipped (at least 3 minutes per inch of thickness) in the preservative. If surface is to be painted, a single coat will be sufficient; otherwise, two or more coats, as the more penetration, the better the protection. Wood coming in contact with the ground or exposed to severe moisture should be soaked thoroughly. Painted surfaces that show rindow should be scraped to remove loose paint. Apply preservative by brush or spray and allow to dry thoroughly, then repaint.

TRUNTS, YANKEELINS, ROPES, LIGHTS, ETC. should be saturated by spray, brush or dip method. If added waterproofing is desired, use 1 lb. of melted paraffin dissolved in each 10 gallons of preservative.

FOR TERMITES ALREADY IN EQUIPMENT. Locate and destroy fungus. Replace badly damaged wood with new treated pieces. Exposed wood should be soaked with preservative, applying generously to joints and cracks. Make a trench around foundation and pilings thirty inches deep and six inches wide, but not below the top of footing if this is shallower. As soil is replaced, add preservative at the rate of four gallons to each five feet of trench.

CONTAINS PETROLEUM DISTILLATE.
 If swallowed, do not induce vomiting. CALL PHYSICIAN IMMEDIATELY.
COMBUSTIBLE. Keep away from heat and open flame. Avoid prolonged contact with skin and breathing of vapor or spray mist. Close container after each use.
 Use with adequate ventilation.
KEEP OUT OF THE REACH OF CHILDREN.

ACCEPTED WITH COMMENTS