

JACCE DTED

ALL 31

JINGER THE PERSONAL INSECTIONS

FOR LUMBRIC POINTS

TO JUNIE W 111

TO A


Stir or shake thoroughly to mix contents. Wood should be dry and free from bark to allow best penetration. Soak wood for a minimum of three minutes or apply, liberally, two or more brush coats. All possibes surfaces should be covered, especially end grains, joints, and those to be in contact with the soil. Fence posts should be soaked in preservative for 12 to 48 hours.

1 GALLON - U.S. MEASURE

CONDITION OF SALE

The following is made in lieu of all warranties, express or implied:

implied:
Seller's only obligation shall be to replace such quantity of
this product proved to be defective. Seller shall not be liable
for any loss or damage, direct or consequential, arising out
of the use of or the inability to use the product. Before
using, user shall determine the suitability of the product for
his intended use, and user assumes all risk and liability
whatsoever in connection therewith. The foregoing may not
be changed except by an agreement signed by an officer
of seller.



DESCRIPTION

A ready-to-use, black wood preservative. Use to control decay and wood rot in fence posts, timbers, posts and beams. Recommended for exterior wood which is not to be painted over. Multiplies the normal life of wood with an easy, quick, and low cost treatment.

Specification Creosote No. 45C meets the requirements for AWPA Grade 1 Creosote.

WARNING: PLANNA La.
Harmful if swallowed, inhaled, or absorbed through skin. Lay cause skin irritation. To not breathe vapor or spray mist. Do not get in eyes, on skir, or on clothing.
Wash thoroughly after handling.
Keep away from heat and open flame.
Use in well ventilated areas.

Cortains flammable solvents.