

**SAP STAIN AND MOLD CONTROL  
FORMULATION  
For  
FRESHLY CUT  
LUMBER and TIMBERS**

**DIRECTIONS FOR USE**

**LUMBER:** For lumber 2 inches or less in thickness, disperse 2.0 to 3.0 lb. (2 to 3 pints) of STA-BRITE LIQUID in 100 U.S. gallons of water. The freshly cut lumber should then be dipped or sprayed in this dispersion until complete surface wetting is accomplished.

**TIMBERS:** For timbers and lumber over 2 inches in thickness, disperse 4.0 to 6.0 lb. (4 to 6 pints) of STA-BRITE LIQUID in 100 U.S. gallons of water and dip or spray in this dispersion until all surfaces are wetted.

E.P.A. Reg. No. 6651-28  
E.P.A. Est. No. 6651-MS-1

Active Ingredients	
2,4-Diacetylmethyl-4-thio-benzothiazole	13.0
2,4-Dichlorophenol	8.8
2,3,4,6-Tetrachlorophenol	1.2
Inert Ingredients	75.0
	100.0

**WARNING  
KEEP OUT OF REACH  
OF CHILDREN**

Harmful or fatal if swallowed or absorbed through the skin. If swallowed, call a physician immediately. Give patient doses of powdered charcoal immediately or all he can swallow of raw egg whites, milk, gruel or flour and water. Then induce vomiting with salt water, or emetic. Do not breathe spray mist. Causes skin irritation. Workmen handling the product or freshly treated lumber, should wear rubber gloves, goggles, and protective clothing and should avoid contact of the product on treated lumber with clothing or skin.

After exposure, wash promptly and thoroughly with an abrasive soap and cool water and finally with glycerin. In case of persistent irritation of the skin, obtain medical attention. Do not get the product into the eyes. If the product gets into the eyes, it causes eye damage, therefore flood eyes immediately with cool water for at least 15 minutes and get medical attention.

Avoid contamination of feed or foodstuffs. Do not use or store near heat or open flame. Keep the drum closed when not in use. Do not reuse empty drum. Return to drum, reconditioner or destroy by perforation or crushing and burying in a safe place.

This product is toxic to fish and wildlife. Keep out of lakes, streams, or ponds. Do not contaminate water by cleaning of equipment or disposal of wastes. Apply this product only as specified on this label.

**A PRODUCT OF**

**SONFORD PRODUCTS CORPORATION**

**GENERAL:** It is desirable that the logs be bright and free from infection at the time they are converted into lumber. For best protection during warm weather lumber should be dipped the day it is sawed, or at least, the following day. STA-BRITE LIQUID should be thoroughly dispersed in water in a mixing tank of known capacity, such as a barrel, prior to being run into the dipping vat. An alternate method of mixing is the Sonford metering device. The dipping vat should be protected from the rain to prevent dilution of the treating dispersion.

Treated lumber and timbers should not be exposed to heavy rains immediately after dipping. Lumber piles should be as narrow as practical, properly elevated, well spaced, and adequately roofed.

**NOTICE:**  
BUYER ASSUMES ALL RISKS OF USE, STORAGE, OR HANDLING IF THIS MATERIAL IS NOT USED IN STRICT ACCORDANCE WITH DIRECTIONS GIVEN HEREWITH.

Net Contents 100 U.S. Gallons