

7424-1

6-2-88

1/2

JASCO®

TERMIN-8

WOOD PRESERVATIVE

GREEN

Seals
Wood

Repels
Water

0901

ACTIVE INGREDIENTS:

COPPER NAPHTHENATE (Equivalent to metallic copper 2%)	25.00%
INERT INGREDIENT	75.00%
TOTAL	100.00%

**KILLS TERMITES
& WOOD EATING INSECTS**

**PREVENTS ROT
FUNGI AND MOLD**

CONTROLS WARPING AND SWELLING

ABOVE OR BELOW GROUND

1 GALLON 3.78 LITERS

EPA EST. 7424-CA-1

EPA REG. No. 7424-1-AA

CAUTION: HARMFUL IF SWALLOWED—KEEP OUT OF REACH OF CHILDREN
See cautions on back panel.

© 1988 JASCO CHEMICALS, INC.

2/2

JASCO TERMIN-8

ABOVE OR BELOW GROUND

JASCO TERMIN-8 conforms to FEDERAL SPECIFICATION TT-W-572, Type II, Composition "C".

SEALS AND PRESERVES WOOD

Stops rot and decay • Fungi and mold
Kills termites and wood eating insects.

WATER REPELLENT

Protects wood from warping, swelling, shrinking, grain raising and checking.

PRIMER

Ideal as an undercoating • Protects paint

Allow a minimum of twenty-four hours drying time before finishing with paint or other coating material. TERMIN-8 may show through the first coat of some light paints.

USES

Use on doors, windows and frames, shingles, stairs, sills, porches, fences, flooring, patio furniture, plywood, etc.

DIRECTIONS

DIP • BRUSH • SPRAY

No protective clothing is necessary unless the user is allergic to Petroleum Distillates. Contents of this container is ready for use after stirring and should not be diluted. Paint, varnish, wax or other films and all bark must be removed before applying TERMIN-8.

All wood to be treated should be normally dry. All unsound wood should be removed at least 2 feet beyond any visible evidence of decay to control termites, carpenter ants, powder post beetles.

Best results can be obtained by soaking the wood for at least three minutes, but when this is not possible at least 2 coats should be applied by either brush or spray. All surfaces should be covered with particular attention paid to end grain and joints.

For fence posts and other wood to be used in contact with the ground, if possible, apply by soaking for 12 to 24 hours covering four to six inches above ground contact; if not, two heavy brush coats within 10 minutes of each other are recommended.

All newly exposed surfaces resulting from cutting, sanding or boring of treated wood should be treated by applying one generous coat of TERMIN-8.

COVERAGE: Approximately seven gallons per 1,000 board feet for open tank treatment depending on wood hardness; approximately 150 to 200 square feet per gallon by spray or brush.

CAUTION! COMBUSTIBLE MIXTURE!

Do not spray or store near heat or open flame. Avoid prolonged or repeated inhalation of mist or contact with skin. Wash with soap and water after handling before eating or smoking. In case of contact with skin or eyes, flush with plenty of water. For eyes, get medical attention. Avoid contamination of food. Do not reuse container. Destroy when empty.

KEEP OUT OF THE REACH OF CHILDREN
NON-PHOTOCHEMICALLY REACTIVE

Max. 350 g/L VOC.

JASCO CHEMICAL CORP.

MOUNTAIN VIEW, CALIFORNIA 94042

CO