

1/1 7995-39 PM-31

CHECK THE FACTS:

GraphCote is recommended only for the racer and only for fiberglass hulls. Although it contains substantial amounts of active ingredients, the presence of graphite reduces anti-fouling effectiveness. Graphite is present in order to facilitate obtaining a tough, racing smooth finish.

GraphCote can be best applied by airless spray. Brush or roller application will increase the amount of surface preparation needed for a super smooth bottom.

Prolonged exposure to air does not reduce the anti-fouling properties. The boat can be launched even a week after application of the final coat.

Can be applied over previously painted surfaces AND DIRECTLY TO FIBERGLASS and EPOXY after an initial sanding to remove release coatings and waxes.



EL 998 GRAPHCOTE	USDA REG NO 998-10
ACTIVE INGREDIENTS	Per Liter
Carbon Dioxide	28.19
Water Soluble of combined fatty	
Acids and Petroleum Acid	
Carbonic Anhydride	21.08
Titanium Dioxide	8.97
TOTAL ACTIVE INGREDIENTS	41.17%
TOTAL INERT INGREDIENTS	58.83%

WARNING: HARMFUL OR FATAL IF SWALLOWED. Contains copper and other toxic substances. Wash thoroughly after handling and before eating or smoking. Do not consume or store near food or food stuffs. Do not use in any household application. Avoid contact with skin and eyes and breathing of vapor or spray mist. May be absorbed through skin. Wash skin with detergent soap then with soap and water. **Combustible.** Keep away from heat and open flame. Use with adequate ventilation. Close container after using.

SUPER RACING GRADE

ANTI-FOULING

Developed for the fiberglass boat owner who races regularly. For use in salt and fresh waters.

KL-990

Graph-Cote

ONE U. S. QUART

KOMPOSITION

The dry coat of KL-990 contains powerful anti-fouling growth inhibitors. It is dried and proven to resist chalking waters.

WARNING: Keep Out of Reach of Children. See side panel for additional precautions.

DIRECTIONS

For maximum results remove old paint layers and apply two full coats, allowing sufficient time for drying between applications. A poorly brushed film will not furnish satisfactory service. GraphCote should be flowed on with a good quality long bristle brush.

Thick, dead layers of old paint will rapidly absorb GraphCote, even for prime coat application. New fiberglass surfaces need a wet sanding before application of the first coat of GraphCote. Application to steel, aluminum and iron surfaces is not recommended. Loose paint, sea growth and dust must be removed from all surfaces to be coated.

The Komposition is easily stirred if the can is inverted and shaken briefly before opening. When ready for application, GraphCote will be uniform in color. Brushes are cleaned easily with mineral spirit.


Before launching, burnish the GraphCote surface with wet fine bronze wool or wet fine sandpaper (#400 or #600 grade). During the season, periodically rub down GraphCote, while wet or while immersed, with a wet turkish towel. Burlap or sandpaper is not recommended as neither will furnish proper polishing results.

For best results allow to dry 6 hours between coats and allow to dry at least 6 hours before launching.

A hull previously coated with GraphCote should be scrubbed immediately upon hauling, using plenty of water and a stiff brush. Re-apply GraphCote when the hull is dry.

One Quart U.S. Standard Measure 946 Liters Metric Measure
5/6's Imperial Quart

U.S. MARINE COATINGS, INC.
SARASOTA, FLORIDA, U.S.A.



BEST AVAILABLE COPY

LITHO IN U.S.A.