

RED

SUPER EPOXYCOP

BY KL-990®

**DEPENDABLE PERFORMANCE
IN WATERS EVERYWHERE**



ONE U.S. GALLON

3.79 L

KEEP OUT OF REACH OF CHILDREN
DANGER

KL-990[®] SUPER EPOXYCOP RED

Super Epoxycop anti-fouling paint combines extremely high levels of Copper and Tin Oxides with an epoxy resin base to provide an excellent anti-foulant paint ideal for fast cruisers and sailboats. This special formulation extends the family of premium products users of KL-990 products have come to expect. Super Epoxycop may be applied over vinyls or certain other hard type anti-fouling paints.

PRECAUTIONARY STATEMENTS

Hazards to Humans and
Domestic Animals

DANGER

Use only with adequate ventilation. Corrosive; causes skin burns. May be dermal sensitizer. Wear protective clothing; e.g., gloves, hat, shirt, and pants. Causes eye irritation. May be fatal if swallowed or inhaled. Harmful if absorbed through skin. Do not breathe vapors or spray mist. Wash thoroughly after use and before eating or smoking.

Practical Treatment. If swallowed, drink promptly a large quantity of milk, egg whites, gelatin solution, or if not available, drink large quantities of water. Get medical attention. Note to M.D.: probable mucosal damage may contraindicate gastric lavage. If in eyes, flush eyes with water. Get medical attention. If on skin, wash with soap and water. Get medical attention. If inhaled, remove victim to fresh air. If not breathing, give mouth-to-mouth respiration. Get medical attention.

ENVIRONMENTAL HAZARD

This product is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill.

PHYSICAL OR CHEMICAL HAZARD

Combustible. Do not use or store near heat or open flame.

EPA Registration #7995-43
EPA Est #7995-MA

GENERAL INFORMATION

Stir thoroughly. Allow at least four hours between coats and before launching. Two coats are recommended for best results. Use only Epoxycop Thinner, if thinning is necessary. Also, use it for cleaning brushes and equipment. Recommended application is 65-85° F. Application in temperature below 60° will unduly extend cure time. Average coverage is 350-400 sq. ft./gal.

DIRECTIONS FOR USE

It is a violation of federal law to use this product
in a manner inconsistent with its labeling.


Fiberglass—New fiberglass must be dewaxed. Epoxycop Thinner is recommended for this purpose. Other suitable solvent or detergent wash may be used. Use KL-990 Sandless Primer before painting or sand with 60 to 100 grit paper. On previously painted bottoms, apply to smooth, clean surface.

Wood—New wood and previously painted bottoms need only be properly sanded. Apply directly to the clean, dry surface.

Metal—Surfaces should be brought to bright metal and degreased with Epoxycop Thinner. Immediately apply two coats of Epoxy Red Lead in accordance with label instructions. Apply to primed surface.

Note: When product is used in confined areas, wear a pesticide respirator jointly approved by the Mining Enforcement and Safety Administration (formerly the U.S. Bureau of Mines) and the National Institute for Occupational Safety and Health under the provisions of 30 CFR 11.

RULE PAINT & CHEMICAL, INC., GLOUCESTER, MA U.S.A. 01930



I
E.

GENERAL DESCRIPTION

Product is an anti-fouling protective coating, resistant to algae, barnacles and other marine fouling. For use in salt and fresh water.

STORAGE & DISPOSAL

Do not contaminate water, food or feed by storage or disposal. Paint that cannot be used according to label instructions must be disposed of according to federal, state or local procedures under the Resources Conservation and Recovery Act. Dispose of container by triple rinse and recycling or disposing in a sanitary landfill or by other approved state and local procedures.

® Registered Trademark

ku