

DO NOT REUSE CONTAINER. DESTROY WHEN EMPTY. DO NOT USE. POUR, SPILL OR STORE NEAR HEAT OR OPEN FLAME.

**ACCEPTED**  
June 18, 1973  
UNDER THE FEDERAL INSECTICIDE  
FUNGICIDE AND RODENTICIDE ACT  
FOR ECONOMIC POISON REGISTER-  
ED UNDER NO. 8120-11

# AMERCOAT

**2035**  
**ANTI-  
FOULING**  
**BLACK**

PROTECTIVE COATING

FORM 2773 (R3/73)

DO NOT CONTAMINATE WATER BY CLEANING OF EQUIPMENT OR DISPOSAL OF WASTES

**DANGER: MAY BE FATAL IF SWALLOWED.  
KEEP OUT OF REACH OF CHILDREN.**

*This product is combustible, toxic and hazardous, especially to the eyes. May be absorbed through skin. Causes skin irritation. Avoid breathing spray mist. Do not get in eyes, on skin or clothing. Use protective clothing, gloves and a fresh air mask, including face protection to prevent contact or breathing of vapors. In case of contact, immediately flush skin with plenty of water; for eyes or other mucous membranes, flush with plenty of water for at least 15 minutes and get medical attention. Wash contaminated clothing before reuse. Keep container closed. Keep away from heat and open flame. See Ameron Corrosion Control Division application instructions included with shipment for equipment and methods recommended for safe application procedure.*

**WARRANTY:** We guarantee the standard quality of this material and its adherence to our published specifications, if any. However, as the use of the product is beyond our control, we expressly disclaim responsibility for its handling, use, storage, the results obtained or any injury or special indirect or consequential damage of any nature whatsoever, however caused.

### APPLICATION INSTRUCTIONS

Stir thoroughly before use. Thin only if necessary, using no more than 1 pint Amercoat No. 7 Thinner per gallon of Anti-Fouling. Spray-apply 2 coats of No. 2035 Anti-Fouling at a coverage not to exceed 300 square feet per gallon for each coat. Allow to dry at least 1/2 hour between coats and 24 hours before placing vessel in water. Clean equipment with Amercoat No. 12 Cleaner.

See additional application instructions accompanying shipment.

No. 2035 ACTIVE INGREDIENTS: Tributyltin Fluoride . . . .	12.6%
INERT INGREDIENTS . . . . .	87.4%
	100.0%
Flash Point . . . . .	90° Tag Open Cup

COMMODITY NO.  
**1351410**  
EPA Reg. No. 8120-11

**Ameron**  
CORROSION CONTROL DIVISION  
Home Office: 201 N. Berry St., Brea, California 92621

NET CONTENTS: 1 U.S. GALLON  
(3.8 LITERS)

**Amercon**  
CORROSION CONTROL DIVISION  
Home Office BREA, CALIFORNIA 92621

CORROSION RESISTANT PRODUCTS

# TECHNICAL DATA SHEET

AND APPLICATION INSTRUCTIONS

This is a development product not for general release. The information contained herein is based on preliminary data and meant to facilitate product evaluation only. Product availability is subject to change without notice.

**TYPE:** Vinyl-Tin Antifouling

**USE:** Shipbottoms

**SUITABLE FOR (SUBSTRATE):** Vinyl--Apply No. 2035 any time after vinyl has dried.

New Polyamide Epoxy--Apply No. 2035 4-24 hours after application of epoxy.

Old Polyamide Epoxy--First, apply 1 coat of Amercoat No. 83 Prime at 1 mil.

Then, apply No. 2035.

**WARNING:** Not suitable over polyAMINE cured epoxies.

**FINISH:** Matte

**COLORS:** White, Black, Oxide Red

**RECOMMENDED DRY FILM THICKNESS:** 2 Mils Per Coat; 2 Coats; 4 Total Mils

**MAXIMUM THEORETICAL COVERAGE:** 600 Mil Sq/Ft. Per Gal.

**NUMBER OF COMPONENTS:** One

**POT LIFE:** Not Applicable

**SURFACE PREPARATION:** New Vinyl--Should be clean and dry. Old Vinyl--Pressure

water hose or sand wash to remove fouling organisms or contamination.

New Polyamide Epoxy--Surface should be clean and dry.

Old Polyamide Epoxy--Same as for old vinyl; apply 1 coat of Amercoat No.

83 Prime, then topcoat with No. 2035 4-24 hours later.

## APPLICATION EQUIPMENT AND INSTRUCTIONS:

**Airless Spray**  
(Graco)

Tip: .615; Pump Pressure: 80-100 psi; Pump Ratio: 28:1

Apply two single-pass coats, overlapping each pass 50%

**Conventional Spray**  
(DeVilbiss MBC)

Cap/Tip: 765 "E"; Pot Pressure: 20 psi;

Gun Pressure: 60 lbs. Apply two cross-spray coats.

Amercoat 2035  
Anti-Fouling

No. 2035

**THINNER (IF REQUIRED DURING APPLICATION):** 1/2 to 1 pint Amercoat 7 Thinner per gallon No. 2035 if using conventional spray; no thinning if using airless spray.

**CLEANER:** Amercoat 12 Cleaner

**FLASH POINT (TOC):** 90°F

**DRYING TIMES:** Between coats of No. 2035 - 1/2 hour @ 70°F  
Before service - 24 hours @ 70°F

**SHIPPING WEIGHT:** Approximately 11.5 lbs. per gallon.

**DANGER:** May be fatal if swallowed. Keep out of reach of children. This product is combustible, toxic and hazardous, especially to the eyes. May be absorbed through skin. Causes skin irritation. Avoid breathing spray mist. Do not get in eyes, on skin or clothing. Use protective clothing, gloves and a fresh air mask including face protection to prevent contact or breathing of vapors. In case of contact, immediately flush skin with plenty of water; for eyes or other mucous membranes, flush with plenty of water for at least 15 minutes and get medical attention. Wash contaminated clothing before reuse. Keep container closed. Keep away from heat and open flame.

Do not re-use container. Destroy when empty. Do not use, pour, spill or store near heat or open flame.

Do not contaminate water by cleaning of equipment or disposal of wastes.

ACCEPTED

June 17, 1973

UNDER THE FEDERAL INSECTICIDE  
FUNGICIDE AND RODENTICIDE ACT  
FOR ECONOMIC POISON REGISTERED  
EPA LABEL NO. 8120-11

ACCEPTED

6-18-73

UNDER THE FEDERAL INSECTICIDE  
FUNGICIDE AND RODENTICIDE ACT  
FOR ECONOMIC POISON REGISTERED  
EPA LABEL NO. 8120-11

R-4/73