VY 5529

Organometallic Anti-Fouling Protective Coating

A Hard Drying Coating Highly Resistant to Algae, Barnacles and Other Marine Fouling

E.P.A. Reg. No. 8928-13

WARNING! FLAMMABLE!

KEEP AWAY FROM HEAT OR OPEN FLAME.

VAPOR HARMFUL

MAY CAUSE SEVERE EYE BURNS

MAY BE FATAL IF SWALLOWED


MAY CAUSE SKIN IRRITATION

KEEP OUT OF REACH OF CHILDREN See other Precautions on right penel.

EXXON CHEMICAL COMPANY U.S.A

An operating division of EXXON CHEMICAL COMPANY, a division of EXXON CORPORATION Houston, TX 77029

NET CONTENTS 5 U.S. GALLONS • 18.9 LITRES Mode in U.S.A.



Precautions

Do not get in eyes, o

Personnel applying the full face air mask and avoid skin and eye conto vapor or mist. Kee open flame. Use with In case of contact, in with plenty of water fland call a physician; of soap and water. clothing before reuse, each use.

Do not contaminate equipment, or dispothis product only as specifically as spe

Directions for Use

Surface should be frand rust. Mix thorough



c Anti-Fouling ting

Resistant to Algae, Barnacles


YLTIN FLUORIDE16.9%

BLE! EAT OR OPEN FLAME.

EYE BURNS
VALLOWED
RITATION
ILDREN

L COMPANY USA

LONS • 18.9 LITRES



Precautions

Do not get in eyes, on skin, or on clothing.

Personnel applying this paint should wear full face air mask and protective clothing to avoid skin and eye contact. Avoid exposure to vapor or mist. Keep away from heat and open flame. Use with adequate ventilation. In case of contact, immediately flush eyes with plenty of water for at least 15 minutes and call a physician; wash skin with plenty of soap and water. Wash contaminated clothing before reuse. Close container after each use.

Do not contaminate water by cleaning of equipment, or disposal of wastes. Apply this product only as specified on this label.

Directions for Use

Surface should be free of all grease, dirt and rust. Mix thoroughly and apply two

coats of RUST-BAN VY 5528 Anti-Fouling Paint over properly primed surfaces. Apply by roller or brush. While thinning is not normally required, RUST-BAN TH 6866 Thinner should be used when necessary.

Allow two hours drying time between coats. Dry film thickness of each anti-fouling coat should be 1.5 mils. Vessel should not be launched in less than six hours after application of final coat of anti-fouling.

Do not reuse containers. Destroy by perforating or crushing container and burying in a safe place.

RUST-BAN VY 5529 Analysis - Wt. %

| Pigment | | 27.7 |
|--------------------------------|-------|-------|
| Active tri-n-butyltin fluoride | | |
| Inerts | 39_ | |
| _ | 100 | |
| Vehicles | ••••• | 72.3 |
| Non-volatiles | 18.4 | |
| Volatiles | 81.6 | |
| | 100.0 | 100.0 |

(G) 5529-a

Trademark Registered