

DEVOE

MARINE

PAINTS & COATINGS · WORLD-WIDE

**34020
ANTI-FOULING
SHIPBOTTOM PAINT
WARNING**

KEEP OUT OF REACH OF CHILDREN

VAPOR HARMFUL - FLAMMABLE

Read Carefully Cautions on Back Panel

FOR USE BY PROFESSIONAL APPLICATORS ONLY

5 U. S. GALLONS

USDA REG. NO. 9461-48

BATCH NO.

© D & R CO. 1963

ACTIVE INGREDIENTS	
Cuprous Oxide	10.0%
Copper Oleate	8.0%
INERT INGREDIENTS	82.0%
	100.0%

DIRECTIONS FOR USE

Be sure that all surfaces are clean, free of moisture, sand, grease or oil, remove all loose paint with wire brush or scraper. Mix thoroughly both by stirring and then pouring from one clean container to another several times. Stir from time to time during application.

Apply one or two coats "as is" on ship bottoms by brush or roller. For spraying, thin if necessary with MD-542 Thinner. Do not add oil or varnishes to this paint. Allow 4 hours between coats.

Anti-Fouling paints must be applied over suitable barrier coats and should not be applied directly to metal. Launching may be accomplished as soon as one hour after the final application but not later than 24 hours after final application.

CAUTION

CONTAINS AROMATIC HYDROCARBONS

Keep away from heat and open flame. Avoid breathing of vapor or spray mist. Avoid contact with skin. Do not take internally. Close container after using.

USE WITH ADEQUATE VENTILATION

MUD-MAF 34020
4 1 69

A Product of
DEVOE & RAYNOLDS CO., INC.

Newark, N. J.

— New Orleans, La. —

San Francisco, Calif.

07105

70117

94104

DEVORE[®] MARINE

PAINTS & COATINGS · WORLD-WIDE

**34020
ANTI-FOULING
SHIPBOTTOM PAINT
WARNING**

KEEP OUT OF REACH OF CHILDREN
VAPOR HARMFUL - FLAMMABLE

Read Carefully Cautions on Back Panel
FOR USE BY PROFESSIONAL APPL CATORS ONLY

5 U. S. GALLONS

USDA REG. NO. 9461-43

ACTIVE INGREDIENTS
Copper Oxide 100%
Copper Oxide 80%
INERT INGREDIENT 20%

100%

D & R CO. 1961

DIRECTIONS FOR USE

Be sure that all surfaces are clean, free of dirt, grease, oil, etc. and remove all loose paint with wire brush or scraper. Mix thoroughly with by stirring and then pouring from one can into the other several times. Stir from time to time during application.

Apply one or two coats (as 87% suspension) with brush or roller, depending, then if necessary with M-24 if needed. Do not mix with other paints in this paint. Allow 2 hours between coats.

Anti-fouling paints must be applied over suitable barrier coat and should not be applied directly to metal. Paints may be reapplied as soon as one hour after the final application, but longer than 24 hours after final application.

CAUTION

CONTAINS AROMATIC HYDROCARBONS

Keep away from heat and open flame. No smoking or fire near this paint. Avoid contact with skin, eyes, nose, mouth, etc. Wash container after using.

USE WITH ADEQUATE VENTILATION

A Product of
DEVORE & RAYNOLDS CO., INC.

Newark, N. J. New Orleans, La. San Francisco, Calif.
Chicago, Ill. Houston, Tex. Los Angeles, Calif.