

# DEVOE

# MARINE

## PAINTS & COATINGS • WORLD-WIDE

**DEV-RAN® FORMULA 214  
ANTI-FOULING  
MD-3407**

**WARNING**  
KEEP OUT OF REACH OF CHILDREN  
**VAPOR HARMFUL—COMBUSTIBLE**  
**HARMFUL OR FATAL IF SWALLOWED**

ACTIVE INGREDIENTS  
Cuprous Oxide 44.25%  
INERT INGREDIENTS 55.75%  
100.0 %

**5 U. S. GALLONS**

Read Carefully Cautions on Back Panel  
FOR USE BY PROFESSIONAL APPLICATORS ONLY

### DIRECTIONS FOR USE

Be sure that all surfaces are clean, free of moisture, scale, grease or oil. Remove all loose paint with wire brush or scraper. Mix thoroughly, both by stirring and then pouring from one clean container into another several times. Stir from time to time during application.

Apply one or two coats "as is" on ship bottom by brush or roller. For spraying, thin if necessary with MD-542 Thinner. Do not add oil or varnishes to this paint. Allow 4 hours between coats.

Anti-Fouling paints must be applied over suitable barrier coats and should not be applied directly to metal. Launching may be accomplished as soon as one hour after the final application but not later than 24 hours after final application.

### WARNING!

**CONTAINS XYLOL, BUTYL ALCOHOL AND CUPROUS OXIDE**

Keep away from heat and open flame. Avoid breathing of vapor and spray mist. Avoid contact with skin. Do not take internally. Close container after using. **FIRST AID:** If swallowed, do NOT induce vomiting. CALL A PHYSICIAN.

USE WITH ADEQUATE VENTILATION

MUD-MAF-3408 10/27/70

*A Product of*

**DEVOE & RAYNOLDS CO., INC.**

Newark, N. J. — New Orleans, La. — San Francisco, Calif.  
07102 70117 94104

ACCEPTED  
4-63  
Pesticide  
Labeling Act  
of 1956  
Registration  
Number 1-63

# DEVORE MARINE

PAINTS & COATINGS · WORLD-WIDE

**DEVORAN<sup>®</sup> FORMULA 214  
ANTI-FOULING  
MD-3407**

**WARNING**  
KEEP OUT OF REACH OF CHILDREN  
**VAPOR HARMFUL—COMBUSTIBLE**  
**HARMFUL OR FATAL IF SWALLOWED**

ACTIVE INGREDIENTS  
Cuprous Oxide 44.25%  
INERT INGREDIENTS 55.75%  
100.00%

## DIRECTIONS FOR USE

Be sure that all surfaces are clean, free of moisture, scale, grease or oil. Remove all loose paint with wire brush or scraper. Mix thoroughly, both by stirring and then pouring from one clean container into another several times. Stir from time to time during application.

Apply one or two coats "as is" on ship bottom by brush or roller. For spraying thin if necessary with MD 542 Thinner. Do not add oil or varnishes to this paint. Allow 4 hours between coats.

Anti-Fouling paints must be applied over suitable barrier coats and should not be applied directly to metal. Launching may be accomplished as soon as one hour after the final application but not later than 24 hours after final application.

## WARNING!

**CONTAINS XYLOL, BUTYL ALCOHOL AND CUPROUS OXIDE**

Keep away from heat and open flame. Avoid breathing of vapor and spray mist. Avoid contact with skin. Do not take internally. Close container after using. **FIRST AID:** If swallowed, do NOT induce vomiting. CALL A PHYSICIAN.

USE WITH ADEQUATE VENTILATION

MUD-MAF 3408 10 27 70

*A Product of*  
**DEVORE & RAYNOLDS CO., INC.**

Newark, N. J. — New Orleans, La. — San Francisco, Calif.  
07105 70117 94104

**5 U. S. GALLONS**

Read Carefully Cautions on Back Panel  
FOR USE BY PROFESSIONAL APPLICATORS ONLY