

WARNING!

**CONTAINS XYLOL, BUTYL
ALCOHOL AND
CUPROUS OXIDE**

DO NOT USE, POUR, SPILL OR
STORE NEAR HEAT OR OPEN
FLAME.

Avoid breathing of vapor or spray
mist.

Avoid contact with skin.

Do not take internally.

Close container after using. Do not
reuse empty container. Destroy it
by perforating or crushing. Bury
or discard in a safe place.

Do not contaminate water by clean-
ing of equipment or disposal of
waste.

FIRST AID: If swallowed, do NOT in-
duce vomiting. CALL A PHYSICIAN.

**USE WITH ADEQUATE
VENTILATION**

DEVOE

MARINE

PAINTS & COATINGS • WORLD-WIDE

**DEVTRAN[®] FORMULA 214
ALLSEAS[®] BLACK ANTI-FOULING
MD-3605**

WARNING!

KEEP OUT OF REACH OF CHILDREN

**COMBUSTIBLE—VAPOR HARMFUL
HARMFUL OR FATAL IF SWALLOWED**

5 U.S. GALLONS

Read Carefully Warning on Left Panel
FOR USE BY PROFESSIONAL APPLICATORS ONLY

| | |
|-----------------------------|---------|
| ACTIVE INGREDIENTS* | |
| Cuprous Oxide | 42.71% |
| Copper Powder | 5.28% |
| INERT INGREDIENTS | 52.01% |
| | 100.00% |

*Equivalent to 43.2%
Metallic Copper

Directions For Use

Be sure that all surfaces are clean,
free of moisture, scale, grease or
oil. Remove all loose paint with
wire brush or scraper. Mix thor-
oughly, both by stirring and then
pouring from one clean container
into another several times. Stir
from time to time during applica-
tion.

Apply one or two coats "as is" on
ship bottom by brush or roller. For
spraying, thin if necessary with
MD-1931 Thinner. Do not add oil or
varnishes to this paint. Allow 4
hours between coats.

Anti-Fouling paints must be ap-
plied over suitable barrier coats
and should not be applied directly
to metal. Launching may be ac-
complished as soon as one hour
after the final application.

MAF 214 625B 6 27 73

**DEVOE & RAYNOLDS
COMPANY, INC.**
NEWARK, NEW JERSEY 07105
NEW ORLEANS, LA 70117
SAN FRANCISCO, CALIF. 94104