

MIL-P-16189B Formula No. 129/63

ACTIVE INGREDIENTS

Cuprous Oxide 62.2%

INERT INGREDIENTS

Lampblack	3.9%
Gum Rosin	10.3%
Vinyl Chloride Resin	2.5%
Tricresyl Phosphate	2.2%
Methyl Isobutyl Ketone	11.1%
Xylene	7.2%
Clay	.6%
Total	100.0%

ANTIDOTE

12 Point

Give **milk** and white of egg beaten with water, then a tablespoon of salt in glass of warm water. If contact is made in eyes, flush with warm water. CALL A PHYSICIAN.

MAY BE FATAL IF SWALLOWED

12 Point

Do not breathe vapor. Do not get in eyes, on skin, or on clothing. Wash thoroughly after handling.

CAUTION COMBUSTIBLE

12 Point

Keep away from heat, sparks, and open flame. Use adequate ventilation. Do not smoke while painting.

Directions and Intended Use. - Formula No. 129/63 vinyl, black anti-fouling paint is intended for use on shipbottom exterior surfaces where a dark colored anti-fouling paint may be required. It should be used alone or preferably over primer, pretreatment (formula 117, MIL-P-15328), on wood or plastic and additionally over vinyl-red lead primer (formula 119, MIL-P-15929) or vinyl-zinc chromate primer (formula 120, MIL-P-15930) on metal. See Bureau of Ships Technical Manual Chapter 9190 for instructions on proper application methods.

Mfd. By
WILLIAM ARMSTRONG SMITH CO.,
EAST POINT, GEORGIA

and wholly owned subsidiary company
RELIANCE CHEMICAL COMPANY
RICHMOND, CALIFORNIA

