

CREOSOTE

ACTIVE INGREDIENT, CREOSOTE INERT INGREDIENT (MAX.)

98.5% 1.5%

EPA REGISTRATION NO. 9639-1-AA

DIRECTIONS FOR USE

Willard Creosote may contain crystals which must be melted by heating the liquid before using. Never dilute. If you do, the effectiveness is reduced. For best results, follow these directions: Heat Willard Creosote to a temperature of 150 F. and stir until all crystals are dissolved. Care should be taken to prevent the creosote from boiling over and catching fire.

HOW TO APPLY AS A WOOD PRESERVATIVE

Brushing: Apply hot Willard Creosote liberally with brush or mop, flooding surface so as to fill completely all cross cuts, mortises, tenons, checks and defects. After an interval of 24 hours or after first application has penetrated, apply a second coat in the same manner to achieve best results. This is absolutely essential for all material to be used under or lying on the ground.

Dipping: It is necessary that all wood to be treated be completely peeled and well seasoned. Immerse that portion of timber to be treated in a bath of hot Willard Creosote for a period of one to two hours. Fence posts, poles, foundation timbers and heavy wooden members should be free of bark, dry and well seasoned and immersed in the product for a period of 12 to 48 hours to be an effective wood preserver.

This product is not to be used in animal sleeping quarters, barns, hog pens, sheep folds and poultry houses.

WARNING: KEEP OUT OF REACH OF CHILDREN

Creosote causes skin irritation. Absorbed through skin. Avoid breathing vapor. Avoid contact with eyes, skin or clothing. In case of contact with skin, wash at once with plenty of soap and water.

DO NOT TAKE INTERNALLY. HARMFUL IF SWALLOWED. See instructions for use before handling. Avoid contamination of feed and foodstuffs.

First Aid: If swallowed, induce vomiting by sticking finger down throat or by giving soapy or strong salty water to drink. Repeat until vomit is clear. Call a physician. Never give anything by mouth to an unconscious person.

Rinse empty container thoroughly with water and discard it.

ONE U.S.GALLON

