

Mobil®

Marine Coating

ANTI-FOULING PAINT FOR METAL BOTTOMS:
Application of two coats is recommended for best performance.

Surface Preparation: Surfaces must be dry, clean, and free of dirt, dust, grease, oil, rust, loose paint and other contaminants. Steel must be coated with suitable primer, or anti-corrosive barrier coats before application of anti-fouling.

Mixing: Before use, power mix or stir the paint until the product is uniform. Stir the paint at intervals during application to maintain uniformity.

Application: Apply by brush, spray, or roller. Do not paint in cold or damp weather.

Thinning: Thin slightly with Thinner T-37 when required for application. Use Thinner T-37 for clean-up.

Coverage: A 2 mil dry film will theoretical spreading rate of 34 per gallon, depending on the used. Actual coverage will be affected by application techniques, job conditions, and condition of surface.

Dry Time: At 70 F and 50% RH, 4 hour dry time between coats of 8 hours before recoating.

Safety: When applied in confined spaces, use proper ventilation and fire extinguishers.

Caution: Do not use in confined spaces. Do not breathe vapors. Wash thoroughly with water by spraying. Do not use in water.

CONTAINS -- ORGANIC SOLVENT

WARNING!

FLAMMABLE (K100, F100)
VAPOR HARMFUL
CAUTION: FUMES



Keep away from heat, sparks, and open flame.
Avoid breathing vapor.
Avoid contact with eyes, skin, and clothing.
Wash thoroughly after handling.

Use in well-ventilated areas.
Wear an air-supplied mask.
Concentrated vapors in enclosed spaces.
Keep containers closed.

FIRST AID: If inhaled, remove to fresh air. If on skin, wash with soap and water. If in eyes, flush with water.

For more information, contact your local distributor or Mobil Chemical Company.

NET 1 GALLON

Mobil Chemical Company

MAINTENANCE & MARINE COATINGS DEPARTMENT
EDISON, N. J. 08817/BEAUMONT, TEX. 77704/KANKAKEE, ILL. 60401/LOS ANGELES, CALIF. 90001

Mobil

Vinyl Anti-Fouling Paint Red 59-R-24

VINYL ANTI-FOULING PAINT RED 59-R-24

ANTI-FOULING INGREDIENTS

ACTIVE INGREDIENTS

Cuprous Oxide	41.6%
Metallic Copper	4.9%

INERT INGREDIENTS	53.5%
-------------------	-------

9-6-73	100.0%
--------	--------

WARNING! See caution elsewhere
on label. (FR-6)

NOTICE: THIS PRODUCT IS FOR INDUSTRIAL USE ONLY
(FR-1) AND IS NOT INTENDED OR SUITABLE FOR USE
IN OR AROUND A HOUSEHOLD OR DWELLING.

EPA Reg. No. 9855-24

EPA Est. 9855-NJ-1