

# Mobil<sup>®</sup>

## Marine Coating

**ANTI-FOULING PAINT FOR METAL BOTTOMS:**  
Application of two coats is recommended for best performance.

**Surface Preparation:** Surfaces must be dry, clean, and free of dirt, dust, grease, oil, rust, loose paint and other contaminants. Steel must be coated with suitable primer, or anti-corrosive barrier coats before application of anti-fouling.

**Mixing:** Before use, power mix or box the paint until the product is uniform. Stir the paint at intervals during application to maintain uniformity.

**Application:** Apply by brush, spray or roller. Do not paint in cold or damp weather.

**Thinning:** Thin slightly with Thinner 7-T-33 when required for application. Use Thinner 7-T-33 for clean-up.

**Coverage:** A 2 mil dry film will be obtained at a theoretical spreading rate of 425-433 sq ft per gallon, depending on the specific application used. Actual coverage will be less due to application techniques, job conditions and condition of surface.

**Dry Time:** At 70°F. and 50% R.H., allow 2 hour dry time between coats, and a total of 4 hours before refloating.

**Safety:** When applied in confined areas, use forced fresh air ventilation. Use fresh air and explosion-proof and non-sparking equipment.

**Caution:** Do not reuse container. Destroy properly when empty. Do not contaminate water by cleaning of equipment, or disposal of wastes.

ML-

CONTAINS — ORGANIC SOLVENT

### WARNING!

FLAMMABLE (EXTREME F TO C)  
VAPOR HARMFUL  
CAUSE IRRITATION



Keep away from heat, sparks, and open flame.  
Avoid breathing vapor.  
Avoid contact with eyes, skin, and clothing.  
Wash thoroughly after handling.

Use with adequate ventilation.  
Wear an air supplied mask to avoid breathing concentrated vapors in enclosed areas.  
Keep container closed.

**FIRST AID:** If inhaled, remove to fresh air. If breathing does not improve, artificial respiration, preferably mouth-to-mouth. Call a physician.

In case of contact, immediately flush eyes profusely with water for at least 15 minutes. Call a physician.

NET 1 GALLON

**Mobil Chemical Company**

MAINTENANCE & MARINE COATINGS DEPARTMENT  
EDISON, N. J. 08817/BEAUMONT, TEX. 77704/KANKAKEE, ILL. 60901/LOS ANGELES, CALIF. 90068