

ANTI-FOULING PAINT FOR METAL BOTTOMS:

Application of two coats is recommended for best performance..

Surface Preparation: Surfaces must be dry, clean, and free of dirt, dust, grease, oil, rust, loose paint and other contaminants.. Steel must be coated with suitable primer, or anti-corrosive barrier coats before application of anti-fouling.

Mixing: Before use, power mix or box the paint until the product is uniform. Stir the paint at intervals during application to maintain uniformity.

Application: Apply by brush, spray or roller. Do not paint in cold or damp weather.

Thinning: Thin slightly with Thinner 7-T-37 when required for application. Use Thinner 7-T-37 for clean-up.

Coverage: A 2 mil dry film will be obtained at a theoretical spreading rate of 475-525 square feet per gallon, depending on the specific product used. Actual coverage will be less due to application techniques, job conditions and condition of surface.

Dry Time: At 70°F. and 50% R.H., allow at least 4 hour dry time between coats, and a minimum of 8 hours before refloating.

Safety: When applied in confined areas, provide forced fresh air ventilation. Use fresh air masks and explosion-proof and non-sparking equipment.

Caution: Do not reuse container. Destroy and properly discard when empty. Do not contaminate water by cleaning of equipment, or disposal of wastes.

ML-327 9-74

CONTAINS — ORGANIC SOLVENT

WARNING!

FLAMMABLE (< 100 F/TCO).
VAPOR HARMFUL
CAUSES IRRITATION



Keep away from heat, sparks, and open flame.
Avoid breathing vapor
Avoid contact with eyes, skin, and clothing.
Wash thoroughly after handling.

Use with adequate ventilation.

Wear an air supplied mask to avoid breathing concentrated vapors in enclosed areas.

Keep container closed.

FIRST AID: If inhaled, remove to fresh air. If not breathing give artificial respiration, preferably mouth-to-mouth. Call a physician.

In case of contact, immediately flush eyes with plenty of water for at least 15 minutes. Call a physician.

Mobil Chemical Company

MAINTENANCE & MARINE COATINGS DEPARTMENT

EDISON, N. J. 08817/BEAUMONT, TEX. 77704/KANKAKEE, ILL. 60901/LOS ANGELES, CALIF. 90058

M I

Vinyl Anti-Fouling
MIL-P-16189 (Formula 12)
Black 559-J-1

ACCEPTED
October 4 1970
9855-28

WARNING! See cautions on label

NOTICE: THIS PRODUCT IS FOR (FR-1) AND IS NOT INTENDED FOR USE IN OR AROUND A HOUSEHOLD

EPA Reg. No. 9855-28

NET 1 GAL