

**ANTI-FOULING PAINT FOR METAL BOTTOMS:**

Application of two coats is recommended for best performance.

**Surface Preparation:** Surfaces must be dry, clean, and free of dirt, dust, grease, oil, rust, loose paint and other contaminants. Steel must be coated with suitable primer, or anti-corrosive barrier coats before application of anti-fouling.

**Mixing:** Before use, power mix or box the paint until the product is uniform. Stir the paint at intervals during application to maintain uniformity.

**Application:** Apply by brush, spray or roller. Do not paint in cold or damp weather.

**Thinning:** Thin slightly with Thinner 7-T-37 when required for application. Use Thinner 7-T-37 for clean-up.

**Coverage:** A 2 mil dry film will be obtained at a theoretical spreading rate of 345-377 square feet per gallon, depending on the specific product used. Actual coverage will be less due to application techniques, job conditions and condition of surface.

**Dry Time:** At 70°F. and 50% R.H., allow at least 4 hour dry time between coats, and a minimum of 8 hours before refloating.

**Safety:** When applied in confined areas, provide forced fresh air ventilation. Use fresh air masks and explosion-proof and non-sparking equipment.

**Caution:** Do not reuse container. Destroy and properly discard when empty.

ML-115 11-73

CONTAINS — ORGANIC SOLVENT

**WARNING!**

FLAMMABLE LIQUID (F+TCO)  
VAPOR HARMFUL  
CAUTION: NO SMOKE



Keep away from heat, sparks, and open flame.  
Avoid breathing vapor.  
Avoid contact with eyes, skin, and clothing.  
Wash thoroughly after handling.

Use with adequate ventilation.

Wear an air-purified mask to avoid breathing concentrated vapors in enclosed areas.

Keep container closed.

**FIRST AID:** If inhaled, remove to fresh air. If not breathing, give artificial respiration, preferably mouth-to-mouth. Call a physician.

In case of contact, immediately flush eyes with plenty of water for at least 15 minutes. Call a physician.

BO-43 4-73

**Mobil Chemical Company**

MAINTENANCE & MARINE COATINGS DEPARTMENT  
EDISON, N. J. 08817/BEAUMONT, TEX. 77704/KANKAKEE, ILL. 60901/LOS ANGELES, CALIF. 90058

**M**

**Shipbot  
Cold Plastic  
MIL-P-19451  
55**

**WARNING!** See caution else  
on label.

NOTICE: THIS PRODUCT  
(FR-1) AND IS NOT IN  
IN OR AROUND

**EPA Reg. No. 9855**