

# PENTA DIP

## clear non-staining wood preservative



**stops rot as it repels insects  
water repellent**

Active Ingredients:  
\*Pentachlorophenol ..... 4.4%  
\*Other Chlorophenols ..... 0.6%  
\*Petroleum Hydrocarbons ..... 81.5%  
Inert Ingredients ..... 13.5%

\*Complies with Fed. Spec.  
TT-W-570A  
\*American Wood Preservers  
Ass'n. Specification P6-51  
EPA Reg. No. 9957-3  
EPA Est. No. 9957-MA-1

**DANGER! COMBUSTIBLE.  
VAPOR HARMFUL  
SKIN & EYE IRRITANT.  
HARMFUL OR FATAL IF SWALLOWED.  
KEEP OUT OF REACH OF CHILDREN.  
see warnings on back panel.**

**ONE U.S. GALLON**

*Jan 9, 1975*

*9957-3*

# PENTA DIP

**CAUTION: Contains petroleum distillate. CALL PHYSICIAN IMMEDIATELY. Do not get in eyes or on skin or clothing. Keep out of reach of children. WASH AFTER HANDLING. May be a skin irritant. Wear rubber gloves and protective clothing when handling treated lumber.**

**This product is toxic to fish and wild birds. Do not use on equipment or disposal of wastes. See instructions on this label.**

**DANGER: COMBUSTIBLE: Do not use in confined areas, provide adequate ventilation (pilot lights, etc.). Close container and transfer contents to bottle or other container when empty.**

**KEEP OUT OF REACH OF CHILDREN**

**PENTA-DIP is a penetrating, clear, water repellent. It is used wherever long life is desired for docks, bridges and highway guard rails. It repels insects and bacteria and wood destroying organisms and bacteria and wood destroying insects such as post beetles and ants. Its effectiveness is not caused by shrinkage, swelling, warping or**

### DIRECTIONS

**PREPARATION: New posts should be cut to length and then cold soaked in a large can or tub for 24 hours. New lumber should be given a heavy coat of Penta-Dip on existing structure. All wood in contact with ground and should have at least two heavy coats. Break all wood-to-earth contacts at ground level. The objective is to establish a treatment barrier. It is suggested that you consult with a professional for application.**  
**APPLICATION: Apply ready-to-use spray. Dries to touch in 2 to 4 hours. Will brush or spray 250 sq. ft. in optimum conditions per 1000 board feet 1-in. thick.**



**STERLING · CLARK · LURTON**

# TA

*Jan 9, 1975*

*9957-3*

# staining servative

as it repels insects  
ellent

**COMBUSTIBLE.**

**IFUL  
IRITANT.**

**FATAL IF SWALLOWED.  
F REACH OF CHILDREN.  
on back panel.**

**GALLON**

# PENTA DIP

**CAUTION:** Contains petroleum distillate. If swallowed, do not induce vomiting. **CALL PHYSICIAN IMMEDIATELY.** Do not breathe vapor or spray mist. Do not get in eyes or on skin or clothing. Keep away from pets, livestock and shrubbery. **WASH AFTER HANDLING.** May be absorbed through skin. May cause skin irritation. Wear rubber gloves and protective clothing when handling freshly treated lumber.

This product is toxic to fish and wildlife. Do not contaminate water by cleaning of equipment or disposal of wastes. Apply this product only as specified on this label.

**DANGER: COMBUSTIBLE:** Do not use near fire or open flame. When using in confined areas, provide adequate ventilation and extinguish all open flames (pilot lights, etc.). Close container after each use. Store in cool place. Do not transfer contents to bottle or other container. Do not reuse container. Destroy when empty.

**KEEP OUT OF REACH OF CHILDREN.**

PENTA-DIP is a penetrating, clear, non-staining wood preservative and water repellent. It is used wherever long service life of wood is desired. On home sills and joists; fence posts, barns and farm buildings; heavy planking and timber for docks, bridges and highway guards. It is highly toxic to wood rotting organisms and bacteria and wood destroying insects such as termites, powder post beetles and ants. Its effective water repellent prevents dimensional changes caused by shrinkage, swelling, warping and grain distortion.

#### DIRECTIONS

**PREPARATION:** New posts should be peeled and seasoned prior to treatment then cold soaked in a large can or oil drum for 48 to 72 hours at each end.

New lumber should be given a heavy brush application as in the case of an existing structure. All wood in contact with the ground is particularly vulnerable and should have at least two heavy brush coats of preservative. For termite control, clean out loose wood or debris under and around infested building.

Break all wood-to-earth contacts and replace with treated wood or cement.

The objective is to establish a treated soil barrier which will prevent termite entry. It is suggested that you consult the State Extension Service for advice.

**APPLICATION:** Apply ready-to-use Penta by dipping, soaking, brush, roller or spray. Dries to touch in 2 to 4 hours. It may be painted after 24 hours. One gallon will brush or spray 250 sq. ft. In open tank dipping, 10 to 15 gals. will be absorbed per 1000 board feet 1-in. thick.



**STERLING·CLARK·LURTON CORP.**

**MALDEN, MASS. 02148**