

PROTECTIVE COATINGS

HEMPEL'S ANTIFOULING III TROPICAL

HEMPEL'S ANTIFOULING III TROPICAL is for temperate waters and is used as an antifouling finish on steel ships' bottoms from keel to light load line. It is composed of a soluble resinous matrix and cuprous oxide which is a poisonous substance.

APPLICATION INSTRUCTIONS: Thoroughly stir and apply 2 coats over Hempel's Platin Primer or Hempel's Anti-corrosive 1. If Hempadur Tar Epoxy is used a sealer coat of Hempel's Platin Primer is required. Allow a 3-5 hour drying time between coats of Hempel's Antifouling III. If thinner is required, use Hempel's Thinner 801 at a ratio not to exceed 10% for brush application and 5% for spray application.

REMARKS: The ship may be floated when the finish is dry to touch (3-5 hours). If exposed to direct sun or high temperature undocking should not be delayed for more than 24 hours. Store in a cool-dry place away from heat, sunlight and open flame.

CLEANING EQUIPMENT: Brushes, rollers and spray equipment should be promptly cleaned with Hempel's Thinner 801.

CAUTION: Keep out of the reach of children. Harmful or fatal if swallowed. Call physician immediately. Contains petroleum distillates. Do not induce vomiting. Combustible (flash point 103 F.) Keep away from heat, open flame and pilot lights. Use with adequate ventilation. Avoid prolonged contact with skin and breathing of vapor or spray mist. Close container after each use.

ACTIVE INGREDIENTS: (CUPROUS OXIDE) 7.5%
INERT INGREDIENTS: 92.5%

100% By Weight

NON-WARRANTY: We guarantee the quality of this product and its conformity to our standard specification as published. However, as the use of this product is beyond our control, we do not warrant, expressed or implied, as to the effects of such use or the results to be obtained if not used in accordance with directions or established safe practice. The buyer must assume all responsibility, including injury or damage, resulting from its misuse as well as in combination with other materials.

NET CONTENTS: 5 U.S. GALS. = 4.163 IMP. GALS.

Made in U.S.A.

USDA Reg. No. 10250-1

