

U. S. D. A. REG. # _____

VINYL PLASTIC ENAMEL

DEEP COPPER #910
(For Anti-Fouling Only)

<u>ACTIVE INGREDIENTS</u>	29.0%
Tributyltin Oxide.....	4.0%
Cuprous Oxide.....	25.0%
	<u>29.0%</u>

<u>INERT INGREDIENTS</u>	71.0%
	<u>100.0%</u>

ACCEPTED
4-10-69
10469-2

SAU-SEA

VINYL PLASTIC ENAMEL

ACCEPTED
APR 10 1969
18769-2

DEEP COPPER #910

WARNING:

KEEP OUT OF REACH OF CHILDREN
See back panel for added cautions!

SUECO SPECIAL PAINTS COMPANY
84 Tecumseh
Medford, New Jersey 08055

CAUTION!

HARMFUL IF SWALLOWED. CALL A DOCTOR AT ONCE. COMBUSTIBLE.

Keep away from heat, sparks or open flame. Do not smoke.
Provide adequate ventilation when painting in confined area.
Avoid contact with skin, eyes or clothing. Avoid breathing of
vapors. Wash thoroughly after using. Keep container closed when
not in use. Keep out of reach of children.

A.C.
4-10-69
10469-2

DIRECTIONS FOR USE

For use on all boat bottoms in fresh or salt water service, long-lasting, where a hard, racing finish is desired. Prepare all surfaces, painted or unpainted: WASH all surfaces and allow thorough drying. SAND all surfaces (including bare surfaces) to provide a clean, firm, uniformly textured surface for painting. WIPE down bare fibre-glass surfaces, if any, with SAU-SEA THINNER #1000 on clean cloth. CAULK AND REPAIR hull, as necessary. Use SAU-SEA CAULKING AND REPAIR PRODUCTS. PRIME: Brush one coat SAU-SEA VINYL MASTIC, BRUSHABLE GRADE on all bare surfaces - including bare spots exposed in the preparation of previously painted surfaces. Allow 12-24 hours for drying. PAINT: Apply one coat SAU-SEA VINYL PLASTIC ENAMEL DEEP COPPER #910 by brush or roller and allow two hours for drying. Apply second coat of enamel and allow 24-48 hours curing time before launch. Cruise when ready. USE ONLY SAU-SEA THINNER WITH SAU-SEA PRODUCTS.