

**CAUTION**  
**CONTAINS:** Toluol and cuprous oxide.  
 If swallowed induce vomiting. **CALL PHYSICIAN IMMEDIATELY.** Do not get in eyes, on skin or clothing. In case of skin or eye contact, flood immediately with plenty of water. For eyes, **CALL PHYSICIAN.** Remove contaminated clothing. Wash clothing before reuse. Avoid contact with skin and vapor or spray mist. Keep away from heat and open flame. Close container after each use. **USE ONLY with ADEQUATE VENTILATION. KEEP OUT OF THE REACH OF CHILDREN.**

**ACCEPTED**  
  
 APR 14 1971  
  
 UNDER THE FEDERAL PESTICIDE  
 FUNGICIDE AND WEEDKILLING ACT  
 FOR ECONOMIC POISON REGISTERED  
 UNDER NO. 10676-1

Manufacturers of  
**POXY PUTTY** Adhesive and Filler  
**SEA GOIN' POXY PUTTY** Applies, cures, holds forever underwater  
**POXY COATING** Anti Corrosive  
**POXY RESIN** Rigid Flexible  
**STAR GLOSS** Polyurethane Varnish  
**PIP** pvc and abs Solvent Cement  
**WIP** Prevents frayed rope ends.

PERMALITE PLASTICS CORPORATION  
 1000 W. 10th Street, Tulsa, Oklahoma 74103



USDA Reg. No. 10676-1



Net Contents: 1 U.S. Quart  
**SEA COAT**  
**RED VL105**

**ANTI-FOULING PAINT**

**ACTIVE INGREDIENTS:**  
 Cuprous Oxide  $Cu_2O$  55%  
 Copper, represented as metallic 47.3%  
**INERT INGREDIENTS:** 45%  
 100%

**WARNING! POISON!**  
**HARMFUL OR FATAL IF SWALLOWED**  
**VAPOR HARMFUL - FLAMMABLE**  
**KEEP OUT OF REACH OF CHILDREN**  
 See further precautions on left panel.

**SEA COAT Anti-Fouling Paint VL 105 - Red** contains cuprous oxide for normal usage. **SEA COAT - Red VL 394** contains cuprous oxide and TBTO for extreme fouling conditions. Both compounds make use of a tough vinyl base, which has excellent adhesion and is especially formulated to give long term leaching action to insure protection. It provides a flexible, tough, smooth film. Ideal for racing or general use. Years of testing under severe growth conditions has proven the excellent resistance of **SEA COAT**. Will adhere to new wood, fiberglass or old paint without the use of a primer. Prime metallic surfaces with one coat Permalite Poxy Coating No. N 181. **SEA COAT** will not deteriorate out of water. May be used on dinghies. For extreme fouling conditions use **SEA COAT VL 394**. See right panel for directions for use.

**DIRECTIONS**  
 Clean bottom and dry thoroughly. New non-metallic surfaces, apply 2 coats **SEA COAT**, allowing 1 hour between coats. New metallic surfaces prime with Permalite N 181, allow 24 hrs. dry time, then apply 1 coat **SEA COAT**. Over existing anti-fouling coat, apply 1 coat **SEA COAT**. Re-paint every 12 months or as needed. Mix completely, apply by brush or roller, cut in water line, then cover from bow to stern. Carry wet edge as you go aft for smooth film. Dries rapidly, boat can be launched 3 hours after painting. Thin with ET 7 only.

