

BRIGHT RED

Sea-worthy™

**ANTI-FOULING
BOTTOM PAINT**

with TBTA*

This new Anti-Fouling Paint is the result of many years of development and testing. The special vinyl resin formulation with TBTA* toxicant assures protection against barnacles, turedos, algae and other marine organisms. The finished coat has remarkable adhesion and is highly resistant to abrasion.

RECOMMENDED FOR: All plywood, wood, fiberglass, aluminum and properly primed steel boats.

FEATURES: TBTA* (Bis Tributyltin Adipate) is a patented development of the 3M Company (U.S. Patent No. 3,236,793) and licensed exclusively to Western Products, Inc. and has proven to be highly effective for extended periods in Florida waters. The vinyl resin formulation provides a hard, low gloss finish, yet allows a true time release or leaching of the toxicant. The time release of TBTA* is functional only when the boat is in the water — even if the boat is trailered and launched on an infrequent basis.

Highly effective with Sea-worthy System for outdrives and underwater propulsion assemblies.

DIRECTIONS

Previous Paint in Good Condition

If old paint is not to be removed and is a vinyl base, the hull should be cleaned thoroughly with fresh water by either high pressure hose or washing down. If necessary, sand lightly to provide better adherence and apply two (2) coats of Sea-worthy Anti-Fouling Paint. If used over sound old copper based paints, sand thoroughly, wash with solvent and apply one (1) coat of Sea-worthy Fiberglass Tie Coat Primer No. 170, per label instructions. Apply two (2) coats of Sea-worthy Anti-Fouling. Check adhesion of old paint with a knife before painting over old finishes.

Fiberglass

- Sand painted surface lightly to provide tooth and wash surface with Sea-worthy Thinner Solvent #632.
- If a new fiberglass hull is to be painted without sanding, wash surface with #636 Fiberglass Hull Prep to remove any traces of dirt, grease, wax and mold release. Apply Sea-worthy Fiberglass Primer #160, allow to dry 30-35 minutes, apply #170 Fiberglass Tie Coat Primer, apply two coats of Sea-worthy Anti-Fouling paint. As an alternate, use Sea-worthy Non-Sanding Fiberglass Primer #180 per label instructions. Apply two coats of Anti-Fouling paint.

Metal Hulls, Outdrives and Propulsion Assemblies

- Prepare aluminum hulls painted with vinyl anti-fouling systems as above for hulls with paint in good condition.
- For sand blasted hulls or new aluminum hulls, clean as above, apply Sea-worthy Metal Primer #110, allow to dry for 30-35 minutes. Apply one coat of Sea-worthy Metal Tie Coat Primer per label instructions, apply two coats Sea-worthy Anti-Fouling paint.
- Aluminum outdrives, rudders, props, struts, etc., with sound non-copper based paints may be cleaned with a high pressure water hose, washed down with #632 Solvent and coated with two coats of Sea-worthy Anti-Fouling paint.
- Outdrives or underwater assemblies such as wheels, props, etc. with new condition vinyl paint should be