

2.31 TRANSTROPIC ANTI-FOULING

BPS ANTI-FOULING PAINT is recommended for use as a bottom paint from keel to light load line on commercial tankers and merchant ships sailing in tropic and temperate waters. It is formulated with a special binder that will slowly leach and release the active ingredients which will inhibit plant growth and is poisonous to hard shell foulants such as barnacles, annelids, mollusks, etc.

DIRECTIONS FOR APPLICATION

Strip old paint thoroughly and apply 1 - 2 coats over BPS Primer #4176 Anti-Corrosive. Allow 2 - 4 hours dry between coats of BPS Anti-Fouling Paint. When the finish is dry to touch, 4 - 6 hours, the ship may be floated. Do not wait longer than 48 hours before floating. If thinner is needed, use BPS Thinner #4178 at 1 pint per gallon. For clean equipment, brushes, rollers, spray equipment, use BPS Cleaner #3146.

ATTENTION: Contains Petroleum Distillate

If swallowed, do not induce vomiting. CALL PHYSICIAN IMMEDIATELY.
Keep away from heat and open flame. Avoid contact with skin and breathing of vapor or spray mist. Harmful if swallowed. Do not use for food use. Do not use empty container. Destroy it by incineration. Do not allow baby or children to play with it.

Net Weight 10.5 lbs. (4.75 kg.) per gallon.

Net Volume 12.5 U.S. Gallons

GUARANTEED
TO GIVE
SATISFACTION
OR PURCHASE PRICE
WILL BE REFUNDED

PATTERSON-SARGENT

A **textron** DIVISION

NORTH BRUNSWICK, NEW JERSEY 08902 - TULSA, OKLAHOMA 74110

2.71 TRANSLONGLIFE ANTI-FOULING

BPS ANTI-FOULING PAINT is recommended for use as a bottom paint from keel to light load line on commercial tankers and merchant ships sailing in tropical and temperate waters. It is formulated with a special binder that will stick and release the active ingredients which will inhibit plant growth and are poisonous to hard shell foulants such as barnacles, annelids, mollusks, etc. Recommended for steel, wood and fiberglass surfaces.

DIRECTIONS FOR APPLICATION

Stir the paint thoroughly and apply 1 - 2 coats over BPS Primer #4187 (Epoxy). Allow 4 - 6 hours dry between coats of BPS Anti-Fouling Paint. When finish is dry to touch, 4 - 6 hours, the ship may be floated. Do not wait more than 48 hours before floating. If thinner is needed, use BPS Thinner #4174 at 1 pint per gallon. Use clean equipment, brushes, rollers, spray equipment. Use BPS Thinner #4174.

Anti-Foulant Contains Petroleum Distillate

If swallowed, do not induce vomiting. CALL PHYSICIAN IMMEDIATELY. COMBUSTIBLE (Flash Point 135°F.). Do not use, pour, spill, or store near open flame. Avoid contact with skin and breathing of vapor or spray. Wash thoroughly if swallowed. Clean container after each use. Do not reuse empty container. Destroy by perforating or crushing. Burn or discard in safe place.

Do not contaminate water, sewer, or other equipment or disposal facilities with wastes.

KEEP OFF OF THE BEACH OF CHILDREN.

GUARANTEED
TO GIVE
SATISFACTION
OR PURCHASE PRICE
WILL BE REFUNDED

PATTERSON-SARGENT

A **textron** DIVISION

NORTH BRUNSWICK, NEW JERSEY 08902 - TULSA, OKLAHOMA 74110