

NEW
SUN

CAUTION:

PROVIDE ADEQUATE VENTILATION.
FLAMMABLE. KEEP AWAY FROM SPARKS
AND OPEN FLAME. PROVIDE A SOURCE
OF FRESH AIR IN ENCLOSED AREAS.

The standard use of this material is
indicated. However, since the use of
this product is beyond our control, we
cannot assume any responsibility for
its use outside of the results obtained
by the manufacturer. For special
concrete management, contact what
soever authority is connected to the
requirements of product.

NR 12

**CHEM-FLEX
No. 1816R
ANTI-FOULANT
COATING**

ACTIVE INGREDIENT

Inhibitor Fluoride 11.5%
Inerts 88.5%

CAUTION
FLAMMABLE
LIQUID!
Keep Away From
Heat or Open
Flame

CAUTION!

**FLAMMABLE!
LIQUID!**

**Keep Away From
Heat or Open
Flame**

1. Avoid contact with eyes, skin and clothing. In case of contact, immediately flush eyes with water for at least 15 minutes. Obtain prompt medical attention. Discard any contaminated clothing.

2. Avoid breathing of vapors when applying in closed areas or during any application. Workers should wear protective equipment including gloves, face and eye shields and air line respirators.

3. Do not re-use empty containers. Destroy by perforating or crushing. Bury or discard in a safe place.

4. Do not use, pour, spill or store near heat or open flame.

DIRECTIONS: Chem-Flex 1816R Anti-Foulant is designed primarily to be applied over Plas-Chem tar epoxy or anti-corrosive vinyl systems. For use specifically over other generic systems, recommendations should be obtained from the manufacturer.

1. Thin Chem-Flex 1816R with 1 pint of Plas-Chem No. 103 Thinner. Mix thoroughly and apply by airless spray. (May be applied by adding an additional 1/2 to 1 pint 103 Thinner to 1 gallon of base for use with conventional spray).

2. Coverage rate shall not exceed 200 square feet per gallon to obtain a minimum of 2 1/2 to 3 mils per application.

3. Apply second coat of Chem-Flex 1816R Anti-Foulant after a minimum of 3-4 hours dry time.

4. Completed system may be put back into service after 6 to 8 hours. Preferably after overnight curing.

PLAS-CHEM CORPORATION
6177 MAPLE, ST. LOUIS, MO. 63130