



# ANTI-FOULING COMPOUND RED

Active Ingredients:	By Wt.
Stannous Oxide	27.1%
Inert Ingredients	72.9%
100% DIBK	100.0%

CAUTION: KEEP OUT OF REACH OF CHILDREN.  
SEE OTHER PRECAUTIONS ON THE BACK LABEL.  
EPA Reg. No. 14826-1

NET 5 GAL.

NAPKO CORPORATION—HOUSTON, TEXAS 77021

CLASSIFICATION  
INTENDED USE

APPLICATION  
THINNING RATIO

COVERAGE  
RECOMMENDED THICKNESS  
DRYING TIME

WEIGHT PER GALLON  
COLOR REFERENCE  
CLEAN UP THINNING

FLASH POINT

CAUTION: Do not use,  
Avoid breathing  
after each use  
DO NOT  
DO NOT CO  
OR DISPOS



# FOULING POUND RED

Ingredients:	By Wt.
Side	27.1%
Ingredients	72.9%
6	100.0%

OUT OF REACH OF CHILDREN.

INSTRUCTIONS ON THE BACK LABEL.  
g. No. 14826-1



**CLASSIFICATION:** Copper - containing Anti-Fouling Compound  
**INTENDED USES:** For use on ship hulls (steel, wood, aluminum, fiber glass) to prevent the growth of marine organisms - one application over a suitable metal primer.  
**APPLICATION:** Brush, Spray or Airless Spray  
**THINNING RATIO:** Brush: As required with Napko 214 Thinner  
Air Spray: Approximately 5:1 with Napko 216  
Airless Spray: Approximately 5:1 with Napko 216  
**COVERAGE:** 257 Sq. ft./gal./ (Theoretical at 3 mil thickness) one application.  
**RECOMMENDED THICKNESS:** Wet: 5.5 mils minimum  
Dry: 3 mils minimum - one application.  
**DRYING TIME:** To touch: 1-2 hours  
To handle: 2-4 hours  
Launch after Coating: 4-8 hours  
**WEIGHT PER GALLON:** 11.4 lbs. - 5.15 kilos (average)  
**COLOR REFERENCE:** Red  
**CLEAN UP THINNER:** Napko 214 or 216  
**FLASH POINT:** 112° F, Pensky-Martens

**CAUTION:** Do not use, pour, spill or store near heat or open flame. Avoid breathing of vapor or spray mist. Close container after each use. Harmful if swallowed.

DO NOT REUSE CONTAINER. DESTROY WHEN EMPTY.  
DO NOT CONTAMINATE WATER BY CLEANING EQUIPMENT,  
OR DISPOSAL OF WASTES.