

PEN-KOTE

Copper Naphthenate

PRESERVATIVE
FOR WOOD - CANVAS - ROPE

ANALYSIS
ACTIVE INGREDIENT
Copper Naphthenate 20%
INERT INGREDIENT 80%
Copper as Metallic 2%

An air-drying, copper-base preservative for wood, fabric, and rope. Will arrest the action of decay, rot fungi, termites and other wood infesting insects. Estimated coverage from 200 to 450 square feet. The natural light green color is not permanent.

DIRECTIONS

Use as it comes from the package. Do not thin. Remove all previous paint coating and cut away rotten wood.

FOR BRUSH OR SPRAY: Apply liberally using as many coats as necessary to insure penetration desired. The degree of protection afforded is dependent upon the amount of preservative that penetrates into the material. At least two coats should be given by brush or spray to all wood that comes into contact with the ground.

FOR DIPS: Length of time for soaking dependent upon thickness of wood to be treated as well as type of wood. A minimum of 15 minutes suggested for members 1/2 inch or less. Overnight soaking is suggested in treating heavier timbers.

FOR CANVAS OR ROPE: Saturate thoroughly. Let dry before using.

SURFACE TO BE PAINTED LATER: Allow 15 hours before painting. If there are knot tints, there may be slight discoloration on first coat but will disappear on second coat if wood is thoroughly dry.

CAUTION KEEP AWAY FROM FIRE. USE IN WELL VENTILATED PLACE.
KEEP OUT OF REACH OF CHILDREN. HARMFUL IF SWALLOWED.
FLASH POINT 110°F. DO NOT USE, POUR, SPILL, OR STORE NEAR HEAT OR OPEN FLAME.
DO NOT REUSE CONTAINER. DESTROY WHEN EMPTY.

This product is toxic to fish. Keep out of lakes, streams, or ponds. Do not contaminate water by cleaning of equipment, or disposal of wastes. Apply this product only as specified on this label.

PEN-KOTE PAINT CO. ■ PENSACOLA, FLORIDA 32509
EPA REG. NO. 31209-1