

Intercide Zinc Naphthenate 1%
Wood Preservative

ACTIVE INGREDIENT:

Zinc Naphthenate.....7.50%
(Zinc as metal- 1%)
Inert Ingredients.....92.50%
Total 100.00%

Keep Out Of Reach Of Children (12 Point)
CAUTION (18 Point)


See Side Panel for Additional Precautionary Statements

EPA Reg. No. 34688-

EPA Est. No. 34688-NJ-1

Net Contents:

Interstab Chemicals, Inc.
500 Jersey Ave
New Brunswick, NJ 08903



Left Panel

PRECAUTIONARY STATEMENTS

HAZARDS TO HUMANS AND DOMESTIC ANIMALS

CAUTION

Harmful if swallowed, inhaled or absorbed through the skin. Do not get in eyes, on skin or on clothing. Wash thoroughly with soap and water after handling.

STATEMENT OF PRACTICAL TREATMENT

IF IN EYES, flush with plenty of water and get medical attention.

IF SWALLOWED, do not induce vomiting. Call a physician immediately.

IF ON SKIN, wash with plenty of soap and water.

ENVIRONMENTAL HAZARDS

This product is toxic to fish. Do not apply directly to water. Do not contaminate by cleaning of equipment or disposal of waste.

PHYSICAL OR CHEMICAL HAZARDS

Do not use or store near heat or open flame.

Right Panel

Directions for Use

It is a violation of Federal law to use this product in a manner inconsistent with its labeling.

STORAGE AND DISPOSAL (12 Point)

Do not contaminate water, food or feed by storage or disposal. Wastes resulting from the use of this product may be disposed of on site or at an approved waste disposal facility.

Container Disposal: Triple rinse or equivalent. Then offer for recycling or reconditioning, or puncture and dispose of in a sanitary landfill, or by other procedures approved by state and local authorities.

Intercide Zinc Naphthenate 1% Wood Preservative is especially formulated to protect wood against common wood destroying fungi and termites. This effective two fold protection greatly extends the beauty and useful life of wood. Since it is a clear product it lets the natural beauty of the wood show through. It can also be painted or stained over which will further extend the life of the wood.

Instructions For Treating Wood

Intercide Zinc Naphthenate 1% is a ready to use product containing Zinc Naphthenate. It contains a petroleum solvent and can be used for treating lumber and heavy timbers. Treatment of wood includes the following representative wooden items: wooden flooring for decks and patios, ladders, door and window frames and sashes, fence posts, stales and small dimensional lumber, wooden siding and shingles, etc. It should be used on heavy structural timbers for above ground use only.

Dip Treatment: Lumber and small wooden structures should be totally immersed in Intercide Zinc Naphthenate 1% treating solution for a period of from 30 seconds to 3 minutes, depending on the thickness of the wood and the absorption required. Heavy lumber items should be dipped for 3 minutes, whereas light and absorptive stakes, window frames, etc. may be sufficiently treated in less time. The treated wood should be drained of excess solution and allowed to air dry until all solvent is gone and the wood is free from solvent odor. This usually takes 24 hours.

Brush Coating and Spraying: Intercide Zinc Naphthenate 1% is ideal for brushing or spraying all types of wood items as discussed above. When using a brush or spraying, coverage should be complete or until runoff starts to occur. After permitting to dry for 24 hours, a second coat may be applied.

Treated dried wood may be painted over if desirable.

Cleaning of Brushes or Spraying Equipment:

Equipment and brushes may be cleaned with mineral spirits or a suitable paint thinner.