

EPA REGISTRATION NO 40238-3

NE®

FOLLOW ALL SAFETY AND HEALTH REGULATIONS PRACTICAL TREATMENT

IF SWALLOWED Do not induce vomiting. If symptoms develop, get medical attention immediately. If symptoms do not develop, drink plenty of water. Do not use emetics.

IF IN EYES Flush with water for 15 minutes. Get medical attention.

IF ON SKIN Wash with plenty of water. Get medical attention.

IF INHALED Remove from exposure immediately. Get medical attention.

WARRANTY The manufacturer warrants that the product conforms to the description on the label.

THERE ARE NO WARRANTIES WHICH EXTEND BEYOND THE DESCRIPTION ON THE FACE HEREOF. IN NO EVENT SHALL PRO LINE BE LIABLE FOR ANY INCIDENTAL SPECIAL OR CONSEQUENTIAL DAMAGES OF ANY NATURE WHATSOEVER INCLUDING WITHOUT LIMITATIONS LOSS OR USE OF LOSS PROFITS.

STORAGE AND DISPOSAL

- 1. **PROHIBITIONS.** Do not contaminate food or water by the storage or disposal of this product.
- 2. **PESTICIDE DISPOSAL.** Follow the approved disposal methods to avoid release of toxic vapors, fumes, and dusts. Do not pour or discharge into any waterway. Do not use in areas where prohibited by Federal, State, or local government.
- 3. **CONTAINER DISPOSAL.** Dispose of approved method.

DIRECTIONS FOR USE OF PRO-LINE #1080-H SERIES

Apply to clean, dry, smooth surfaces. Stir well before using. THE SURFACE MUST BE FREE OF ALL SURFACE CONTAMINATION AND MOISTURE.

**HARD VINYL ANTIFOULING PAINT
PRO-LINE 1080-H**

APPLICATION Mix thoroughly. Stir well before using.

ALUMINUM Clean surface with acetone. Apply 1 coat.

STEEL Clean surface with acetone. Apply 1 coat. MARINE BOND™ epoxy primer and Epoxies are recommended. Apply 1 coat of Epoxies 48 hours before applying PRO-LINE 1080-H.

FIBERGLASS HULL UNPAINTED Clean surface with water and TSP. Apply 1 coat. Apply 1 coat of Epoxies 48 hours before applying PRO-LINE 1080-H.

WOOD Clean surface with acetone. Apply 1 coat. PRO-LINE 1080-H can be applied over Epoxies.

OLD ANTIFOULING Must be removed. Apply 1 coat. Apply 1 coat of Epoxies 48 hours before applying PRO-LINE 1080-H.

FERRO CEMENT Clean surface.

RECOAT TIME 24 hours between coats.

LAUNCH TIME 30 days after application.

THINNING Use only as directed.

NOTE: When antifouling is applied over Epoxy Primers, the antifouling must be applied within 3-5 hours after last coat of Epoxy Primer.

PRO-LINE 1080-H is a hard vinyl antifouling paint. It is designed to provide long-term protection against fouling.

**NON-PHOTOCHEMICALLY REACTIVE
PRO-LINE PAINT MANUFACTURING CO.**

PHONE (619) 232-8968

LONG BEACH (213) 432-7961