

ACCEPTED  
 JAN 0-2 1987  
 Federal Insecticide,  
 Fungicide, and Rodenticide Act,  
 as amended for the pesticide  
 under the pesticide  
 EPA Reg. No. 45726-1

**PRECAUTIONARY STATEMENTS  
 PHYSICAL HAZARDS**

Keep away from heat and open flame

**Combustible**

**HAZARDS TO HUMANS AND DOMESTIC  
 ANIMALS - WARNING**

Harmful or fatal if swallowed. Causes eye irritation. Do not get in eyes. Use with adequate ventilation. Avoid contact with skin and breathing of vapor or spray mist. Close container after each use. Do not transfer contents to bottles or other unlabeled containers. Wear goggles or face shield and rubber gloves when handling. Use protective breathing mask and protective clothing when spraying or sanding.

When used in enclosed areas, while spraying paint, or sanding boat surface, wear a mask or a respirator jointly approved by the Mining Enforcement and Safety Administration and the National Institute for Occupational Safety and Health.

**FIRST AID:** If swallowed: Drink promptly a large quantity of milk, egg whites, gelatin solution or, if these are not available, drink large quantities of water. Avoid alcohol. Get medical attention. If in eyes: Flush with plenty of water. Get medical attention. If on skin: Wash with plenty of soap and water. Get medical attention. If inhaled: Remove victim to fresh air. If not breathing, give artificial respiration preferably mouth-to-mouth. Get medical attention.

**Use Only With Adequate Ventilation**

KEEP OUT OF REACH OF CHILDREN  
**WARNING**  
 See side panel for additional precautionary statements.

**FORMULA**

**7**

**ANTIFOULING BLACK**  
 AN EPOXY COATING FOR  
 FIBERGLASS AND WOOD

EPA REG. NO. 45726-1

Active Ingredient	% BY WT
Cuprous Oxide	54.18
Other Ingredients	45.82
	100.00
Ethyl Methacrylate	48.12

Contains Petroleum Distillate  
 A non-photochemically reactive solvent blend

**SPECIALTY MARINE COATINGS**  
 209 Ardmore Road  
 FAYETTEVILLE, TENNESSEE 37334  
 (615) 433-1571  
 One U.S. Quart

**STORAGE AND DISPOSAL**

**STORAGE**-Cool and dry and keep away from flame.  
**DISPOSAL**-Triple rinse (or equivalent) and offer for recycling or reconditioning, or dispose of in a sanitary landfill, or by other approved State and local procedures. Pesticide, spray mixture, or rinseate that cannot be used according to label instructions must be disposed of according to applicable Federal, state, or local procedures.

**ENVIRONMENTAL HAZARDS**

This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill.

**INGREDIENTS FOR FORMULA 7**

Formula 7 contains cuprous oxide, aliphatic hydrocarbons, ethylene glycol monoethyl ether acetate, epoxy resin, lamp black, graphite, zinc oxide, talc, and miscellaneous driers and additives. Ethylene Glycol Monobutyl Ether

**PREPARATION FOR RACING FINISH by  
 SANDING FORMULA 7**

Formula 7 will provide a durable smooth antifouling racing finish. Start by using wet dry sandpaper (220 grit). Use some liquid detergent in the water to keep the paper open and work up to 600 grit wet dry. Buffing or burnishing may also be done for a smoother finish.

**DIRECTIONS FOR USE**

It is a violation of Federal law to use this product in a manner inconsistent with its labeling.

**For Salt and Fresh Water Use**

For application to vessels subject to attack by barnacles, algae, tube worms, and other fouling organisms.

**For Wood and Fiberglass Boats**

Formula 7 may be applied by brush, rolling, or spraying. Allow 6 hours to overnight to dry between each coat. Reduce with mineral spirits to desired consistency for application of a smooth coat. Apply two to three coats. One (1) quart will cover about 150 square feet at 1.0 mils.

Launch within 48 hours after application of final coat. Paint should be dry to touch before immersion.

**FOR FIBERGLASS**

Formula #7 Antifouling Paint may be applied directly to well sanded and cleaned fiberglass without use of a primer. Sanding of fiberglass for good adhesion is required.

**WOODEN BOTTOMS (UNFINISHED WOOD)**

Reduce with mineral spirits for application of first coat. Apply second and third coats unreduced.

**WOOD AND FIBERGLASS BOTTOMS  
 (OLD WORK)**

Remove all traces of loose paint, dirt, grease, etc. Sand the existing paint film well and apply two coats of Formula #7 Antifouling Paint.