

Please read instructions on reverse before completing form.

Form Approved. OMB No. 2070-0060. Approval expires 2-28-95



United States Environmental Protection Agency Washington, DC 20460

Registration Amendment Other

OPP Identifier Number

225786

Application for Pesticide - Section I

1. Company/Product Number 60061-12
2. EPA Product Manager Marion Johnson
3. Proposed Classification None
4. Company/Product (Name) Z\*Spar Supertox TE Hard Type Antifouling Paint B-70 Red
5. Name and Address of Applicant Kop-Coat, Inc. 436 Seventh Avenue Pittsburgh, PA 15219
6. Expedited Review. In accordance with FIFRA Section 3(c)(3)(b)(i), my product is similar or identical in composition and labeling to: EPA Reg. No. Product Name

Section - II

Amendment - Explain below. Resubmission in response to Agency letter dated. Notification - Explain below. Final printed labels in response to Agency letter dated. "Me Too" Application. Other - Explain below.

Explanation: Use additional page(s) if necessary. (For section I and Section II.)

Notification of alternate brand name:

Woolsey/Z\*Spar Super Tox Anti-Fouling Finish B-70 Red

NOTIFICATION OCT 4 1996


Section - III

1. Material This Product Will Be Packaged In: Child-Resistant Packaging, Unit Packaging, Water Soluble Packaging, 2. Type of Container: Metal, Plastic, Glass, Paper, Other (Specify). 3. Location of Net Contents Information: Label, Container. 4. Size(s) Retail Container: 1 quart, 1 gallon, 5 gallon. 5. Location of Label Directions: On Label, On Labeling accompanying product. 6. Manner in Which Label is Affixed to Product: Lithograph, Paper glued, Stenciled, Other.

Section - IV

1. Contact Point (Complete items directly below for identification of individual to be contacted, if necessary, to process this application.) Name: ALAN S. ROSS Title: VICE PRESIDENT Telephone No.: 412-826-3387. Certification: I certify that the statements I have made on this form and all attachments thereto are true, accurate and complete. 2. Signature: Alan S. Ross 3. Title: VICE PRESIDENT 4. Typed Name: ALAN S. ROSS 5. Date: September 20, 1996 6. Date Application Received (Stamped)

# Woolsey®/Z★SPAN



## SUPER TOX

Anti-Fouling Finish

### B-70 RED

NET CONTENTS  
1 GALLON (3.785 LITERS)



Keep Out of Reach of Children

**WARNING**

Causes eye irritation

Keep out of reach of children

Causes eye irritation

Keep out of reach of children



7<sup>3</sup>/<sub>8</sub> 50410 K  
10-17-95

50410 C  
10-17-95

50410 M  
10-17-95

# SPAR

# OX

# D

(S)



**SUPER TOX ANTIFOULING PAINT:** A highly effective hard antifouling bottom paint. Protects against attachment of barnacles, hydroids, bryozoa, algae and other marine or fresh water growths. Protects wood boats against borers. For use in both salt and fresh water. Do not apply to any surfaces other than boat bottoms.

**DIRECTIONS FOR USE:**

It is a violation of Federal Law to use this product in a manner inconsistent with its labeling.

**GENERAL:** Be sure surface is clean and dry before painting. When sanding is necessary on surfaces, remove sanding dust by clean air blast, clean soft brushes or wiping with clean rags, then follow by tack rag wipe to insure complete removal of sanding dust.

**NOTE:** Face mask should be used when sanding. Stir paint well before and during use. Apply generously with brush or roller at package consistency. If thinning is necessary due to evaporation of solvent from the can, use Z★Spar T-10 Thinner. Do not apply at temperatures below 40°F, or if rain is expected before coating is dry.

**COVERAGE PER COAT:** Approximately 425 sq. ft. per gallon (allows for a 20% loss).

**NUMBER OF COATS:** 2 or 3 depending on the surface.

**DRYING TIME AT 70°F AND 50% RELATIVE HUMIDITY:** Between coats: 6 hours minimum.

Prior to launching: 6 hours minimum to overnight, preferably: 7 days maximum.

**THINNER:** Z★Spar T-10 Thinner

**CLEANER:** Z★Spar T-8, T-10, or T-11 Thinner.

**OLD BOTTOM PAINTS:** After hauling the boat, allow the hull to dry thoroughly of absorbed water before repainting. Over old paint, for best results apply two coats of SUPER TOX after scrubbing, cleaning and removing any loose paint. When sanding old bottom paint, always WET SAND and take precautions against getting the material in your eyes, nostrils, open cuts, etc. Where excess bottom substrate is visible, prime per instructions for the substrate.

**WOOD BOTTOMS:** Sand wood surface with 80-100 grit wet or dry sandpaper. Apply three coats of SUPER TOX paint to bare wood. Thin first coat 10% with Z★Spar T-10 Thinner to allow greater penetration. The next two coats should be applied at package consistency. Any metal parts must be properly primed before applying the bottom paint.

**FIBERGLASS BOTTOMS:** Wash fiberglass with soap, ammonia and water. Rinse thoroughly and let dry. Then thoroughly clean hull with Woolsey 624 Dewaxer. Sand thoroughly with 80 grit sandpaper to dull and roughen the surface. Wipe off sanding dust with a clean cloth or tack rag. Apply two or three coats of SUPER TOX.

For prevention and repair of bottom blisters apply at least three coats of Woolsey 340 Gold Epoxy Primer. Read the appropriate product technical data sheets for surface preparation and application details before

applying the barrier system.

**STEEL BOTTOMS:** Sandblast to a near white metal surface or better, and apply three coats of Woolsey 340 Gold Primer to a minimum of 12 mils dry film thickness. For best results, apply the first coat of SUPER TOX 'wet on wet' to the last coat of Epoxy Primer (usually between 2 to 6 hours). If the primer cures longer than overnight but less than 36 hours, apply another coat of primer and use 'wet on wet' technique. If the primer cures longer than 36 hours it must be sanded with 80 grit sandpaper prior to the application of SUPER TOX.

**ALUMINUM BOTTOMS:** SUPER TOX ANTIFOULING PAINT is not recommended for aluminum.

**STORAGE AND DISPOSAL**

**STORAGE:** Keep closures tight and upright to prevent leakage. Keep container closed when not in use. In case of spillage, absorb and dispose of in accordance with local applicable regulations.

**PESTICIDE DISPOSAL:** Do not contaminate water, food or feed by storage or disposal. Pesticide wastes are toxic. Improper disposal of excess pesticide, spray mixture or rinsate is a violation of Federal law. If these wastes cannot be disposed of by use according to label instructions, contact your State Pesticide or Environmental Control Agency, or the Hazardous Waste representative at the nearest EPA Regional Office for guidance.

**CONTAINER DISPOSAL:** Triple-rinse (or equivalent). Then offer for recycling or reconditioning, or puncture and dispose of in a sanitary landfill, or by other procedures approved by state and local authorities.

**PRECAUTIONARY STATEMENTS  
HAZARDS TO HUMANS  
AND DOMESTIC ANIMALS  
WARNING**

**CONTAINS AROMATIC AND ALIPHATIC HYDROCARBONS, ALCOHOL AND ACETATES.**

**See Material Safety Sheet for this product.**

Do not get on skin, in eyes or on clothing. Wear goggles or face shield and protective clothing such as long-sleeved cotton shirt, long pants, hat and rubber gloves when handling. Wash thoroughly with soap and water after handling. Remove contaminated clothing and wash before reuse. Do not breathe sanding dust, vapor or spray mist. Do not take internally.

**STATEMENT OF PRACTICAL TREATMENT**

**In case of skin contact, wash thoroughly with soap and water; for eyes, flush**

**WARRANTY:** We guarantee this material to comply with our published specifications. Since the use of this material is beyond our control, we do not warrant the results obtained or any injury or damage of any nature resulting therefrom.

Manufactured by Kop-Coat, Inc., Woolsey/Z★Spar Division, Rockaway, NJ 07866  
Product Emergencies 1-800-548-0489

3  
4  
4

**SUPER TOX ANTIFOULING PAINT:** A highly effective hard antifouling bottom paint. Protects against attachment of barnacles, hydroids, bryozoa, algae and other marine or fresh water growths. Protects wood boats against borers. For use in both salt and fresh water. Do not apply to any surfaces other than boat bottoms.

**DIRECTIONS FOR USE:**

It is a violation of Federal Law to use this product in a manner inconsistent with its labeling.

**GENERAL:** Be sure surface is clean and dry before painting. When sanding is necessary on surfaces, remove sanding dust by clean air blast, clean soft brushes or wiping with clean rags, then follow by tack rag wipe to insure complete removal of sanding dust.

**NOTE:** Face mask should be used when sanding. Stir paint well before and during use. Apply generously with brush or roller at package consistency. If thinning is necessary due to evaporation of solvent from the can, use Z\*Spar T-10 Thinner. Do not apply at temperatures below 40°F, or if rain is expected before coating is dry.

**COVERAGE PER COAT:** Approximately 425 sq. ft. per gallon (allows for a 20% loss).

**NUMBER OF COATS:** 2 or 3 depending on the surface.

**DRYING TIME AT 70°F AND 50% RELATIVE HUMIDITY:** Between coats: 6 hours minimum.

Prior to launching: 6 hours minimum to overnight, preferably: 7 days maximum.

**THINNER:** Z\*Spar T-10 Thinner

**CLEANER:** Z\*Spar T-8, T-10, or T-11 Thinner.

**OLD BOTTOM PAINTS:** After hauling the boat, allow the hull to dry thoroughly of absorbed water before repainting. Over old paint, for best results apply two coats of SUPER TOX after scrubbing, cleaning and removing any loose paint. When sanding old bottom paint, always WET SAND and take precautions against getting the material in your eyes, nostrils, open cuts, etc. Where excess bottom substrate is visible, prime per instructions for the substrate.

**WOOD BOTTOMS:** Sand wood surface with 80-100 grit wet or dry sandpaper. Apply three coats of SUPER TOX paint to bare wood. Thin first coat 10% with Z\*Spar T-10 Thinner to allow greater penetration. The next two coats should be applied at package consistency. Any metal parts must be properly primed before applying the bottom paint.

**FIBERGLASS BOTTOMS:** Wash fiberglass with soap, ammonia and water. Rinse thoroughly and let dry. Then thoroughly clean hull with Woolsey 624 Dewaxer. Sand thoroughly with 80 grit sandpaper to dull and roughen the surface. Wipe off sanding dust with a clean cloth or tack rag. Apply two or three coats of SUPER TOX.

For prevention and repair of bottom blisters apply at least three coats of Woolsey 340 Gold Epoxy Primer. Read the appropriate product technical data sheets for surface preparation and application details before

applying the barrier system.

**STEEL BOTTOMS:** Sandblast to a near white metal surface or better, and apply three coats of Woolsey 340 Gold Primer to a minimum of 12 mils dry film thickness. For best results, apply the first coat of SUPER TOX 'wet on wet' to the last coat of Epoxy Primer (usually between 2 to 6 hours). If the primer cures longer than overnight but less than 36 hours, apply another coat of primer and use 'wet on wet' technique. If the primer cures longer than 36 hours it must be sanded with 80 grit sandpaper prior to the application of SUPER TOX.

**ALUMINUM BOTTOMS:** SUPER TOX ANTIFOULING PAINT is not recommended for aluminum.

**STORAGE AND DISPOSAL**

**STORAGE:** Keep closures tight and upright to prevent leakage. Keep container closed when not in use. In case of spillage, absorb and dispose of in accordance with local applicable regulations.

**PESTICIDE DISPOSAL:** Do not contaminate water, food or feed by storage or disposal. Pesticide wastes are toxic. Improper disposal of excess pesticide, spray mixture or rinsate is a violation of Federal law. If these wastes cannot be disposed of by use according to label instructions, contact your State Pesticide or Environmental Control Agency, or the Hazardous Waste representative at the nearest EPA Regional Office for guidance.

**CONTAINER DISPOSAL:** Triple rinse (or equivalent). Then offer for recycling or reconditioning, or puncture and dispose of in a sanitary landfill, or by other procedures approved by state and local authorities.

**PRECAUTIONARY STATEMENTS  
HAZARDS TO HUMANS  
AND DOMESTIC ANIMALS  
WARNING**

**CONTAINS AROMATIC AND ALIPHATIC HYDROCARBONS, ALCOHOL AND ACETATES.**

**See Material Safety Sheet for this product.**

Do not get on skin, in eyes or on clothing. Wear goggles or face shield and protective clothing such as long-sleeved cotton shirt, long pants, hat and rubber gloves when handling. Wash thoroughly with soap and water after handling. Remove contaminated clothing and wash before reuse. Do not breathe sanding dust, vapor or spray mist. Do not take internally.

**STATEMENT OF PRACTICAL TREATMENT**

**In case of skin contact, wash thoroughly with soap and water; for eyes, flush**

immediately with plenty of water for 15 minutes and call a physician. **If affected by breathing of vapor, move to fresh air.** If not breathing, give artificial respiration, preferably mouth-to-mouth. **If swallowed, drink promptly a large quantity of milk, egg white, gelatin solution or if these are not available, drink large quantities of water. Avoid alcohol. CALL A PHYSICIAN IMMEDIATELY. NOTE TO PHYSICIAN:** Probable mucosal damage may contraindicate the use of gastric lavage.

**KEEP OUT OF REACH OF CHILDREN. Use with adequate ventilation during application and drying.**

In tanks and other confined areas, use only with adequate forced air ventilation to prevent dangerous concentrations of vapors which could cause death from explosion or from breathing. When product is used in confined areas or while sanding boat surfaces, wear a mask or a respirator jointly approved by the Mining Enforcement and Safety Administration (U.S. Bureau of Mines) and the National Institute for Occupational Safety and Health under the provision of 30CFR 11. Prevent flames, sparks, welding, and smoking.

**PHYSICAL OR CHEMICAL HAZARDS**  
Flammable. Keep away from heat and open flame.

**ENVIRONMENTAL HAZARDS**

This material is toxic to fish. Do not apply directly to water. Do not contaminate water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during the paint removal to enter water. Dispose of paint debris in an approved landfill.

**IN CASE OF FIRE:** Use dry chemical, foam, water fog or CO<sub>2</sub>. Cool closed containers with water.

Non-Photochemically Reactive.

**WARRANTY:** We guarantee this material to comply with our published specifications. Since the use of this material is beyond our control, we disclaim responsibility for its handling, use, storage, the results obtained or any injury or damage of any nature resulting therein.

Manufactured by Kop-Coat, Inc., Woolsey/Z\*Spar Division, Rockaway, NJ 07866  
Product Emergencies 1-800-548-0489

An **RPM** Company

4  
4  
4