

PETTIT

marine  paint

ACCEPTED

MAR 11 1999

Under the Federal Insecticide, Fungicide, and
Rodenticide Act as amended, for the
pesticide, registered under
EPA Reg. No. 60061-58

DISCLAIMER: The performance of any marine paint or coating depends on many factors outside the control of Pettit Paint Company, including surface preparation, proper application and environmental conditions. Therefore, Pettit Paint Company cannot guarantee this product's suitability for your particular purpose of application. Implied warranties of fitness for a particular purpose and of merchantability are excluded. Pettit Paint Company shall not under any circumstances be liable for incidental or consequential damages. By purchase or use of this product, buyer agrees that the sole and exclusive remedy, if any, is limited to the refund of the purchase price or replacement of the product at Pettit Paint's option.

Uinepoxy

PLUS

ANTIFOULING BOTTOM PAINT

- High copper content.
- Economical antifouling protection.
- Hard, smooth finish.
- Apply over most other antifoulants.
- Excellent for fiberglass, wood, steel boats.

1518 BROWN

NET CONTENTS
1 GALLON (128 FL. OZ.)
3.785 LITERS

COMMERCIAL AND NON-COMMERCIAL USE
KEEP OUT OF REACH OF CHILDREN.

WARNING

SEE BACK PANEL FOR ADDITIONAL PRECAUTIONARY STATEMENTS.

ACTIVE INGREDIENT:

Cuprous Oxide 52.6%

INERT INGREDIENTS 47.4%

100.00%

COPPER AS METALLIC 46.7%

EPA REGISTRATION NO. 60061-58
EPA EST. NO. 60061-NJ-2

This product contains petroleum distillates.



7 25469 0026 1 6

KOP-COAT, INC.
PETTIT PAINT DIV.
ROCKAWAY, NJ 07866 An **RPM** Company

Kop-C
n, Kop-

60061-58
3/11/1999
Page 1 of 2

**PRECAUTIONARY STATEMENTS
HAZARDS TO HUMANS AND DOMESTIC ANIMALS**

WARNING: Causes eye irritation. Harmful if absorbed through skin. Avoid contact with skin, eyes or clothing. Wear protective clothing such as gloves, long-sleeved cotton shirt, long pants and hat. May be fatal if swallowed or inhaled. Do not breathe vapors, spray mist or sanding dust. Wear a MSHA/NIOSH certified mask or respirator. Remove contaminated clothing and wash before reuse. Wash thoroughly with soap and water after handling.

STATEMENT OF PRACTICAL TREATMENT

IF SWALLOWED: Drink promptly a large quantity of milk, egg whites, gelatin solution or, if these are not available, drink large quantities of water. Avoid alcohol. Get medical attention.

IN EYES: Flush eyes with plenty of soap and water. Call physician if irritation persists.

ON SKIN: Wash with plenty of soap and water. Get medical attention.

IF INHALED: Remove victim to fresh air. If not breathing, give artificial respiration, preferably mouth-to-mouth. Get medical attention.

ENVIRONMENTAL HAZARDS: This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes or allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill.

PHYSICAL OR CHEMICAL HAZARDS: FLAMMABLE! Keep away from heat, sparks, and open flame. Use only with adequate ventilation during mixing, application and drying. Use absorbent clean-up material if spilled. For fires, blanket flames with foam, CO₂ or dry chemical. Wear MSHA/NIOSH certified breathing equipment.

DIRECTIONS FOR USE

It is a violation of Federal law to use this product in a manner inconsistent with its labeling.

GENERAL DESCRIPTION: Pettit Unepoxy Plus is an antifouling protective coating resistant to algae, barnacles and other marine fouling.

STORAGE & DISPOSAL: Do not contaminate water, food, or feed by storage or disposal. Open dumping is prohibited.

PESTICIDE DISPOSAL: Pesticide wastes are toxic. Improper disposal of excess pesticides, spray mixture or rinsate is a violation of Federal Law. If these wastes cannot be disposed of by use according to label instructions, contact your State Pesticide or Environmental Control Agency, or hazardous waste representative of the nearest EPA Regional Office for guidance.

CONTAINER DISPOSAL: Triple rinse (or equivalent). Then offer for recycling or reconditioning, or puncture and dispose of in a sanitary landfill or by other procedures approved by State and local authorities.

Product Description: Unepoxy Plus is a hard protective antifouling paint for use on boat bottoms. It is resistant to barnacles, algae, grass and other forms of marine and freshwater fouling. Unepoxy Plus may be applied on fiberglass as well as wood or properly primed steel boats. Unepoxy Plus is also suitable for non-aluminum trailered boats since its hard finish is resistant to abrasion.

Compatibility: Unepoxy Plus may be applied over most aged hard antifouling coatings. Old soft antifouling paints must be completely removed before applying Unepoxy Plus. Old tin copolymers must be removed completely or sealed with Pettit 6627 Tie Coat Primer before applying Unepoxy Plus.

Mixing: Unepoxy Plus is heavily loaded with cuprous oxide. As a result of this loading there is a tendency for settling to occur especially if the paint has been on the shelf for several months. It is necessary to thoroughly mix the paint before using. If possible shake the can of paint on a mechanical paint shaker. Before using check the sides and bottom of the can to make sure all the pigment has been mixed in. If mixing is going to be done with a wooden paddle or an electric drill mixer, pour off half of the liquid from the top of the can into another can and then properly mix in any settled pigments, then remix the two parts together thoroughly.

Application Temperatures: 50°F and above.

Application Method: Brush, roller or spray.

Thinner: Thinning Unepoxy Plus is not normally required. If necessary, use Pettit 12120 Brushing Thinner for brush and roller applications, or Pettit 12121 Spraying Thinner for spray applications. In

either case, do not thin more than 5% by volume.

Coverage: Unepoxy Plus covers approximately 400 square feet per gallon.

Number of Coats: Two full coats of Unepoxy Plus are recommended for best antifouling protection.

Dry Times:	To recoat	To launch
90°F	2 hours	8 hours
70°F	4 hours	16 hours
50°F	6 hours	24 hours

The above dry times are minimums. Unepoxy Plus may be recoated after the minimum times shown and launched up to 60 days after painting.

VOC: Less than 375 g/l unthinned. Less than 400 g/l thinned.

PAINT SYSTEMS

The paint systems outlined below contain references to other Pettit products. Please read and understand the label and/or Technical Bulletin for these products as well to ensure that they are used properly. For further guidance, please contact your local Pettit salesman or the Pettit Customer Service Department at (800) 221-4466 between the hours of 8:30 a.m. and 4:30 p.m. EST.

Previously Painted Surfaces: If the previous coating is in good condition, thoroughly sand with 80 grit production paper and wipe clean with a rag dampened with Pettit 12120 Brushing Thinner to remove sanding residue. Apply two coats of Unepoxy Plus observing the proper dry times. If the previous coating is soft or in poor condition, remove to the bare surface by sanding or using paint and varnish remover. Proceed with the appropriate bare system as described below. Old tin copolymer paints must be removed or may be sealed with Pettit 6627 Tie Coat Primer before applying Unepoxy Plus.

Bare Fiberglass: All bare fiberglass, regardless of age, must be thoroughly cleaned using Pettit 15095 Fiberglass Dewaxer and clean lint-free rags. Several cleanings may be necessary to ensure complete removal of contaminants. Change rags frequently during the dewaxing/cleaning process to ensure complete removal of contaminants rather than merely smearing them on the surface. New boats must be scrubbed with a detergent and water solution and rinsed with fresh water prior to dewaxing. After the surface has been dewaxed, sand it thoroughly with 80 grit production paper and rewash the sanded surfaces with Pettit 15095 Dewaxer or 12120 Brushing Thinner to remove sanding residue. Apply two coats of Unepoxy Plus observing the proper dry times.

If sanding is prohibited, as with certain vinyl-ester gelcoats, or is otherwise impractical, make sure the surface has been completely and thoroughly dewaxed and cleaned with Pettit 15095 Fiberglass Dewaxer. Then apply one thin continuous coat of Pettit 6999 Sandless Primer. Topcoat with two coats of Unepoxy Plus carefully following the topcoating instructions on the Sandless Primer label.

Bare Wood: Sand the entire surface with 80 grit production paper and wipe clean with a rag dampened with Pettit 12120 Brushing Thinner. Apply a coat of Unepoxy Plus thinned 5% with the 12120 Brushing Thinner to penetrate and seal the wood. Fill any open seams with Pettit Seam Compound (7110 White or 7610 Mahogany) and allow to dry overnight. Apply two full coats of Unepoxy Plus observing the proper dry times.

Steel Hulls, Underwater Metal Parts and Keels: For steel hulls and metal keels, consult Pettit Technical Bulletin TB430 High Build Epoxy Primer for complete priming instructions. For underwater metal parts, consult Technical Bulletin TB112 Underwater Running Gear Painting Specification for complete priming and application details.

Maintenance of Antifouling Paint: No antifouling paint can be effective under all conditions of exposure. Man-made pollution and natural occurrences can adversely affect antifouling paint performance. Extreme hot and cold water temperatures, silt, dirt, oil, brackish water and even electrolysis can ruin an antifouling paint. Therefore, we strongly suggest that the bottom of the boat be checked regularly to make sure it is clean and that no growth is occurring. Lightly scrub the bottom with a soft brush to remove anything from the antifouling paint surface.

Warranty: We guarantee this material to comply with our published specifications. Since the use of this material is beyond our control, we disclaim responsibility for its handling, use, storage, the results obtained or any injury or damage of any nature resulting therein.

DO NOT USE THIS PRODUCT ON ALUMINUM HULLS OR OUTDRIVES

MEDICAL EMERGENCIES:

1-800-548-0489



282