ACCEPTED

JUL 1 6 2002

Under the Federal Insecticide, Fungicide, and Rodenticide Act as amended, for the pesticide, registered under EPA Reg. No. 60661-63

DISCLAIMER: The performance of any DISCLAIMENT The performance of any marine paints or coating depends on many factors outside the control of Pettit Paint Company including surface preparation; propeg application and environmental conditions. Therefore, Pettit Paint Company cannot guarantee this product's suitability for your particular purpose or applications. Implied warranties of fitness for a particular purpose or applications. Implied warranties of fitness for a particular purpose and of merchantability are excluded. Petric Paint Company shall not under any circumstances be liable for incidental or consequential damages. By purpose or use of frisapproducts buyer agrees that the sole and exclusive remedy: it any, is limited to the refunction the purchase price of replacementation product at Petrit Paint's option.

> **NET CONTENTS** 1 GAL. (128 FL. OZ) 3.785 LITERS

ANTIFOULING BOTTOM PAINT

- Economical Antifouling Protection
- Hard Smooth Finish
- Apply Over Most Other Antifoulings
- Excellent For Fiberglass, Wood & Steel Boats

NON-COMMERCIAL USE KEEP OUT OF REACH OF CHILDREN. WARNING

SEE BACK PANEL FOR ADDITIONAL PRECAUTIONARY STATEMENTS.



ACTIVE INGREDIENT: Cuprous Oxide

INERT INGREDIENTS

45.7% <u>54.3%</u> 100.0%

40.6%

COPPER AS METALLIC

Total

This product contains petroleum distillates.

EPA EST, NO. 80061-NJ-2 EPA REGISTRATION NO. 60061-83



UNEPOXY STANDARD

PRODUCT DESCRIPTION: Unepoxy Standard is a hard protective antifouling paint for use on boat bottoms. It can be applied over most aged hard antifouling coatings. Old soft antifouling paints should be removed for best adhesion. It may be applied on fiberglass boats with outboards or outdrives with no danger of electrolysis, provided the drive units are not coated themselves. Unepoxy Standard is also suitable for all Non-Aluminum trailered boats.

PREPARATION OF SURFACE: The surface to be painted should be dry, clean and oil free. It should be properly prepared by sanding and solvent cleaning before any primers or paints are applied. Follow the recommended systems below. When sanding old antifouling paint use a face mask to prevent the inhalation of sanding dust.

APPLICATION AND TEMPERATURE: Unepoxy Standard can be applied by brush, roller or spray. The work should be done between 9:00 a.m. and 4:00 p.m. under good drying conditions. The temperature range of application is 40° to 90°F. Two coats should be applied for best antifouling protection.

PREPARATION OF PAINT: Unepoxy Standard is heavily loaded with cuprous oxide. As a a result of this loading there is a tendency for settling to occur especially if the paint has been on the shelf for several months. It is necessary to thoroughly mix the paint before using. If possible shake the can of paint on a mechanical paint shaker. Before using check the sides and bottom of the can to make sure all the pigment has been mixed in. If mixing is going to be done with a wooden pade led or an electric drill mixer pour off half of the liquid from the top of the can into another can and then properly mix in any settled pigment, then remix the two parts together thoroughly.

THINNER: Thinning Unepoxy Standard is not normally required. If necessary use Pettit 120 Brushing Thinner for a smoother finish on especially warm and breezy days. Use Pettit 121 Spraying Thinner for spray application. Use either thinner for clean-up. After the second coat is applied, let the paint dry at least eight hours or preferally overnight before immersing the boat. Under adverse drying conditions let the boat dry overnight to make sure all the solvent is out of the paint film. Maximum dry time before launching is two months.

COVERAGE: Unepoxy Standard covers approximately 400 square feet per gallon.

MAINTENANCE OF ANTIFOULING PAINT: No antifouling paint can be effective under all conditions of exposure. Manmade pollution and natural occurrences can adversely affect antifouling paint performance. Extreme hot and cold water temperatures, silt, dirt, oil, brackish water and even electrolysis can ruin an antifouling paint. Therefore, we strongly suggest that the bottom of the boat be checked several times a month to make sure it is clean and that no growth is occurring. Lightly scrub the bottom with a soft brush to remove anything from the antifouling paint surface.

PAINT SYSTEMS

Previously Painted Surfaces: If the previous coating is in good condition, thoroughly sand with 8C grit paper then solvent clean with 120 Brushing Thinner to remove residue. Apply two finish costs of Unepoxy Standard. If the previous coating is soft or in poor condition, remove to the bare surface by sanding or using a paint or varnish remover. Proceed with appropriate bare system as described below. Old tin copolymers should be removed or sealed with Pettit 65?? The Coat Primer before applying Unepoxy Standard.

Bare Fiberglass: All bare fiberglass, regardless of age, should be thoroughly cleaned several times with Pettit 95 Dewaxer or 120 Brushing Thinner. Sand thoroughly with 80 grit sandpaper to a dull, frosty finish and rewash the sanded surface with 95 Fiberglass Dewaxer or 120 Brushing Thinner to remove sanding residue. Then apply two coats of Unepoxy Standard, following application instructions. Careful observation of the above instructions will help ensure long term adhesion of this and subsequent years' antifouling paint. To effaint the sanding operation, wash the fiberglass three times using Pettit 95 Dewaxer only. Then apply one coat of Pettit 6999 Sandless Primer. Consult the Sandless Primer label for complete application and antifouling topcoating instructions.

Bare Weed: Sand entire surface with 80 grit paper; wash clean with 120 Brushing Thinner. Apply a coat of Unepoxy Standard thinned 25% with 120 Brushing Thinner, allow an overnight dry, lightly sand and wipe clean, Apply two finish coats of Unepoxy Standard.

Steel Hulls, Underwater Metal Parts, Lead Keets: For steel hulls and metal keels consult Pettit Technical Bulletin TB 430 High Build Epoxy Primer for complete priming instructions. For underwater metal parts and running gear, use Pettit 6456 Underwater Metal Kit which includes complete priming materials and instructions for use.

DO NOT USE THIS PRODUCT ON ALUMINUM HULLS AND OUTDRIVES

WARNING! THIS PRODUCT CONTAINS A CHEMICAL KNOWN TO THE STATE OF CALIFORNIA TO CAUSE CANCER. BIRTH DEFECTS, OR OTHER REPRODUCTIVE HARM.

PRECAUTIONARY STATEMENTS HAZARDS TO HUMANS AND DOMESTIC ANIMALS

WARNING: Causes eye irritation. Harmful if absorbed through skin. Avoid contact with skin, eyes or clothing. Wear protective clothing such as gloves, long-sleeved cotton shirt, long pants and hat. May be fatal if swalfowed or inhaled. Do not breathe sanding dust, vapor or spray mist. Remove contaminated clothing and wash clothing before reuse. Wash thoroughly with soap and water after handling.

STATEMENT OF PRACTICAL TREATMENT: IF SWALLOWED: Drink promptly a large quantity of milk, egg whites, gelatin solution or, if these are not available, drink large quantities of water. Avoid alcohol, Get medical attention.

IF IN EYES: Flush with plenty of water. Get medical attention.

IF ON SKIN: Wash with plenty of soap and water. Get medical attention.

IF INHALED: Remove victim to fresh air. If not breathing, give artificial respiration, preferably mouth-to-mouth. Get medical attention

ENVIRONMENTAL HAZARDS: This material is toxic to fish. Do not apply directly to water by cleaning of equipment or disposal of wastes. Do not allow chips and dust generated during paint removal to enter water. Dispose of paint debris in an approved landfill.

PHYSICAL OR CHEMICAL HAZARD: COMBUSTIBLE! Do not use or store near heat or open flame.

DIRECTIONS FOR USE

It is a violation of federal law to use this product in a manner inconsistent with its labeling. NOTE: When product is used in confined areas or applied by spraying, wear a respirator jointly approved by the Mining Enforcement and Safety Administration (formerly the U.S. Bureau of Mines) and by the National Institute for Occupational Safety and Health under the provision of 30 CFR 11

GENERAL DESCRIPTION

Unepoxy Standard is an antifouling protective coating resistant to algae, barnacles and other marine fouling.

STORAGE AND DISPOSAL: Do not contaminate water, food or feed by storage or disposal. Open dumping is prohibited.

PENTICIDE DISPOSAL: Pesticide wastes are toxic. Improper disposal of excess pesticide, spray minutur. or rinsate is a violation of Federal Law. If these wastes cannot be disposed of by use according to lable instructions, contact your state Pesticide or Environmental Control Agency, or the Hazardous Waste representative of the nearest EPA Regional Office for guidance.

CONTAINER DISPOSAL: Triple rinse (or equivalent). Then offer for recycling or reconditioning, or puncture and dispose of in a sanitary landfill, or by other procedures approved by state and local authorities.

MEDICAL EMERGENCIES: 1-800-548-0489

MADE IN USA P3003 1228GA 10/00